

Lubrizol

PERFORMANCE COATINGS



BIO-BASED WAX ADDITIVES FOR COATINGS AND INKS

BIO-BASED WAX TECHNOLOGIES

Addressing the growing demand for raw materials that deliver sustainability benefits and reduce the environmental impact of coatings and inks, Lubrizol offers a selection of wax technologies with bio-based content. These raw materials include micronized powders and liquid dispersions/emulsions designed for use in a range of applications. They are fully or partially based on waxes from plant-based or animal sources, which decrease the consumption of fossil resources and help improve the carbon footprint of coatings and inks without sacrificing performance. We continue to develop our range of bio-based waxes. Please contact us to discuss latest status and availability, and hear about the specific properties of new grades.

MICRONIZED

PRODUCT NAME	POLYMER TYPE	BIO-BASED % OF SOLIDS	PARTICLE SIZE μm		MELTING POINT °C (°F)	DENSITY g/cm ³ @ 20°C	COATING TYPES				PRODUCT NAME	PERFORMANCE BENEFITS					OTHER PROPERTIES/BENEFITS
			DV50	DV90			WATER-BORNE	SOLVENT-BORNE	POWDER	RADIATION-CURED		COF REDUCTION (SLIP)	SCRATCH & ABRASION RESISTANCE	MATTING	SILKY FEEL	ANTI-BLOCKING NON-STICKING	
Lanco™ 1380 F	Modified Polypropylene Wax	25-50	≤9	≤22	150 (302)	0.95	●	●	○	●	Lanco™ 1380 F	○	●	●	○	●	Burnish resistance.
Lanco™ 1380 SF	Modified Polypropylene Wax	25-50	≤6	≤14	150 (302)	0.95	●	●	○	●	Lanco™ 1380 SF	○	○	○	●	●	For thin film applications.
Lanco™ 1400 SF	Modified Amide Wax	25-50	≤6	≤14	140 (284)	0.97	○	●	●	○	Lanco™ 1400 SF	●	○	○	●	○	Excellent surface feel.
Lanco™ 1410 LF	Modified Amide Wax	25-50	≤9	≤19	140 (284)	0.97	●	●	●	○	Lanco™ 1410 LF	○	○	○	●	●	Good compatibility in water-based systems.
Lanco™ 1955 SF	Carnauba Wax	≥ 90	≤6	≤14	82 (190)	0.99	●	●	○	○	Lanco™ 1955 SF	●	●			●	Good release properties. Acid value <15.
Lanco™ 2510 SF	Inorganically Modified Wax Compound	25-50	≤6	≤14	105(221)	1.05	●	●	○	○	Lanco™ 2510 SF	○	●	○		○	Excellent abrasion resistance for PTFE-free formulations.
Lanco™ 2520 SF	Inorganically Modified Wax Compound	25-50	≤6	≤14	105(221)	1.07	●	●	○	○	Lanco™ 2520 SF	○	●	○		○	Excellent abrasion resistance for PTFE-free formulations.
Lanco™ 2520 EF	Inorganically Modified Wax Compound	25-50	≤5	≤10	105(221)	1.07	●	●	○	○	Lanco™ 2520 EF	●	●	○		○	Excellent abrasion resistance for PTFE-free formulations.
Lanco™ A 1602	Fatty Acid Amide Wax	≥ 90	≤9	≤22	142 (288)	0.99	○	●	●	○	Lanco™ A 1602	○	○	●	○	●	Good sanding properties for wood coatings.
Lanco™ A 1603	Vegetable Based Amide Wax	≥ 90	≤6	≤14	142 (288)	0.99	○	●	●	○	Lanco™ A 1603	○	○	○	●	●	Excellent release in can coatings.
Lanco™ Flow P 30	Hydrogenated Castor Oil	≥ 90	≤20	≤80	87 (189)	1.00			●		Lanco™ Flow P 30						Degassing and wetting aid for powder coatings.
Lanco™ PE 1544 F	Modified Polyethylene Wax	25-50	≤9	≤22	140 (284)	0.99	●	●	●	○	Lanco™ PE 1544 F	○	○	●		○	
Lanco™ PE 1554 SF	Modified Carnauba Wax	25-50	≤6	≤14	104 (219)	0.96	○	●			Lanco™ PE 1554 SF	●	●			○	Suitable for coil coatings.
Lanco™ PP 1362 D	Modified Polypropylene Wax	25-50	≤9	≤22	140 (284)	0.94	●	●	○	●	Lanco™ PP 1362 D	○	●	●	○	●	Excellent multi-purpose wax.
Lanco™ PP 1362 SF	Modified Polypropylene Wax	25-50	≤6	≤14	140 (284)	0.94	●	●	○	●	Lanco™ PP 1362 SF	○	○	○	●	●	For thin film applications.
Lanco™ SM 2003	Modified Amide Wax	25-50	≤9	≤22	140 (284)	0.97	○	●	●	○	Lanco™ SM 2003	●	○	●	○	○	Good overall performance in wood coatings. Good degassing in powder coatings.
PowderAdd™ 9060	Amide Wax	≥ 90	≤9	≤22	140 (284)	0.99			●		PowderAdd™ 9060	○					Degassing in powder coatings.
PowderAdd™ 9062	Modified Amide Wax	25-50	≤80		140 (284)	0.97			●		PowderAdd™ 9062	○	○				Degassing in powder coatings.
PowderAdd™ 9421	Proprietary Polymer	51-89	≤7	≤14	80 (176)	0.097			●		PowderAdd™ 9421	○					Degassing in powder coatings. Suitable for low bake systems.
PowderAdd™ 9423	Proprietary Polymer	51-89	≤7.5	≤16	140 (284)	0.094			●		PowderAdd™ 9423	○					Degassing in powder coatings.

● premium performance ○ good performance

Please contact your local account manager or customer service member to find out about availability and specific properties of new grades in development.

DISPERSIONS

PRODUCT NAME	POLYMER TYPE	SOLIDS (%)	BIO-BASED % OF SOLIDS	SOLVENT	PARTICLE SIZE μm		MELTING POINT	DENSITY	PRODUCT NAME	COATING TYPES		PERFORMANCE BENEFITS				OTHER PROPERTIES/BENEFITS
					DV50	DV90	$^{\circ}\text{C}$ ($^{\circ}\text{F}$)	g/cm^3 @ 20°C		WATER-BORNE	SOLVENT-BORNE	COF REDUCTION (SLIP)	SCRATCH & ABRASION RESISTANCE	RUB/ABRASION RESISTANCE	ANTI-BLOCKING NON-STICKING	
Lanco™ Glidd 4415	Carnauba Wax	15	≥ 90	Alcohol, Glycol Ether, Aromatic 150 ND	3	6	82 (180)	0.91	Lanco™ Glidd 4415		●	●	●		●	Good gloss retention.
Lanco™ Glidd 4838	Modified Carnauba Wax	38	≥ 90	Butyl Glycol/Isobutanol	3	7.5	82 (180)	0.92	Lanco™ Glidd 4838		●	●	●		●	Excellent gloss retention.
Lanco™ Glidd 5350	Modified Carnauba Wax	30	≥ 90	Butyl Glycol	3.5	6.5	82 (180)	0.91	Lanco™ Glidd 5350	●	●	●				Meat release effect in can coatings.
Lanco™ Glidd 5518	Modified Carnauba Wax	18	≥ 90	Butyl Glycol	3	7	82 (180)	0.92	Lanco™ Glidd 5518	●	●	●	●	○		Good gloss retention.
Lanco™ Glidd 6502	Polyethylene/Carnauba Wax	27	51-89	Water/Butyl Glycol	4.5	9.5	112(234)	0.97	Lanco™ Glidd 6502	●		●	●	○	●	Good gloss retention.
Lanco™ Glidd BT	Carnauba Wax	15	≥ 90	Glycol Ether	3.5	8	82 (180)	0.96	Lanco™ Glidd BT	●	●	●	●	○	●	

● premium performance ○ good performance

Wax dispersions are a combination of natural and/or synthetic polymers that are mechanically dispersed in organic solvents, water or other liquid carriers using a variety of media mills or high-speed Cowles dispersion techniques.



EMULSIONS

PRODUCT NAME	PRODUCT TYPE	SOLIDS (%)	BIO-BASED % OF SOLIDS	pH	MELTING POINT °C (°F)		PRODUCT NAME	IONIC CHARACTER	COF REDUCTION (SLIP)	BLOCK RESISTANCE	SCRATCH ABRASION RESISTANCE	OTHER PROPERTIES/ BENEFITS
Aquaslip™ 912	T1 Carnauba Wax	25	51-89	6	81 (178)		Aquaslip™ 912	Anionic	●	○	●	
Aquaslip™ 942	T3 Carnauba Wax	25	51-89	8.4	81 (178)		Aquaslip™ 942	Non-Ionic	●	○	●	
Aquaslip™ 952	T1 Carnauba Wax	25	51-89	9	81 (178)		Aquaslip™ 952	Non-Ionic	●	○	●	
Aquaslip™ 958	Proprietary Wax Combination	27.5	25-50	6.6			Aquaslip™ 958	Non-Ionic	●	○	●	Good release properties.

● premium performance ○ good performance

Wax emulsions are a stable mixture of one or more natural or synthetic waxes in water. Emulsions always contain a wetting agent package adjusted to the appropriate HLB value depending on the wax being emulsified. Processing is performed at temperatures above the melt point of the wax. If the wax melt point is above the boiling point of water, the emulsion must be processed under pressure to prevent the water from boiling.



NORTH AMERICA

Lubrizol Advanced Materials, Inc.
9911 Brecksville Road
Brecksville, OH 44141 USA
+1.888.234.2436

EUROPE

Lubrizol Deutschland GmbH
Max-Planck-Str. 6
27721 Ritterhude Germany
+49.421.69333

ASIA-PACIFIC

Lubrizol Specialty Chemicals
(Shanghai) Co., Ltd
10/F, Park Center International
No. 1088 Fang Dian Road
Shanghai 201204, PR China
+8621.3866.0366

SOUTH AMERICA

Lubrizol do Brasil Aditivos Ltda
Avenida Nove de Julho, 3653
Jardim Paulista
Sao Paulo – SP
01407-000
+55.11.4097.0250

Visit us at:

www.lubrizol.com/coatings

WHAT WE ADD MAKES THE DIFFERENCE.™

Lubrizol Performance Coatings is a market-driven innovator of specialty chemicals for advanced coatings, inks and composites that enable the world to move cleaner, create smarter and live better. Our portfolio of resin and additive technologies solve challenges across a wide range of markets and applications. Formulators choose Lubrizol to achieve unique durability, functionality, sustainability and aesthetic capabilities. More than just a supplier, we are a collaborator with extensive experience in surface protection, dispersion, adhesion, and barrier properties – working closely with customers to explore and develop truly differentiated solutions.



The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Product safety information required for safe use is not included. **BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LUBRIZOL REPRESENTATIVE, OR DISTRIBUTOR.**