

Lubrizol

PERFORMANCE COATINGS



THERMOPLASTICS
& THERMOSETS





DISPERSANTS
PRODUCT
GUIDE FOR
PLASTICS

HYPERDISPERSANTS FOR THERMOPLASTICS AND THERMOSETS

Solplus™ and Solsperse™ hyperdispersants and coupling agents have been developed to meet the needs of the plastic industry, for both thermoplastic and thermoset polymers, as well as polyurethanes.

THERMOPLASTIC MASTERBATCH AND COMPOUNDING

Solplus™ DP310 hyperdispersant is recommended for the dispersion of organic and inorganic pigments and fillers in thermoplastic masterbatch and compound applications. It can be used in a variety of thermoplastic polymers including polyethylene, polypropylene, polystyrene, ABS and PVC.



PLASTICIZER AND POLYOL DISPERSIONS

The recommended Solplus™ hyperdispersant for the production of plasticizer and polyol dispersions is dependent upon the pigment:

Solplus™ K500	Inorganic pigments and fillers
Solplus™ DP700	Inorganic pigment fillers and carbon black
Solplus™ K200	Organic pigment (phthalate free dispersions)
Solplus™ K210	Organic pigments (phthalate based dispersions)
Solplus™ R700	Organic pigments (polyether polyols)
Solplus™ R710	Organic pigments (polyether polyols)

BENEFITS

In both phthalate and non-phthalate plasticizer systems and in polyether and polyester polyols for conversion to polyurethanes, Solplus hyperdispersants improve dispersion of:

- Organic and inorganic pigments
- Fillers
- Flame retardants
- Stabilizers
- Blowing agents

As a result, manufacturers achieve:

- Higher solids loadings/increased pigment concentration
- Reduced viscosities (more Newtonian rheology)
- Improved color strength development
- Better dispersion of color in finished polymer
- Cost reductions (increased productivity and fewer passes on the mill)



THERMOSET/COMPOSITE APPLICATIONS

Engineered specifically for composite fillers and resins—and based on proprietary polymer chemistry—Solplus™ additives offer major process advantages to the thermoset industry, including the combination of dispersing/wetting and anti-settling benefits in a single additive.

From being 100% active and solvent free, Solplus™ hyperdispersants also help to reduce environmental impact from the styrene content levels that characterize most unsaturated polyester based systems.

Solplus™ dispersants have been developed to improve dispersion of fillers, flame retardants and reinforcements (fibers) in thermoset systems, as well as for organic and inorganic pigments in gel coats.


BENEFITS

- Higher filler/flame retardant loadings
- Decreased viscosities
- Anti-settling
- Improved stability
- Improved color to white compatibility
- Improved processing

HYPERDISPERSANTS AND COUPLING AGENTS FOR THERMOPLASTICS AND THERMOSETS

INFLUENCE OF MEDIA COMPATIBILITY ON PRODUCT SELECTION

For a Solsperse™ or Solplus™ hyperdispersant to be effective in specific applications, it must be compatible with the media in which the solid is being dispersed AND have an affinity with the surface of the material itself. These are the main criteria used in product selection. The main grades offered for a range of plastics applications are mapped out below:



*Solplus™ F100 is an air-release agent that is designed for rapid air-release and effective wetting in thermoset systems.

With certain organic pigment dispersions it may be advantageous to include the use of a Solsperse™ synergist in combination with the polymeric Solplus™ or Solsperse™ hyperdispersant.

FORMULATING GUIDELINES

DOSAGE – PLASTIC APPLICATIONS

MASTERBATCH/COMPOUND

To determine the optimum dosage for masterbatch or compound applications, a “ladder series” should be carried out.

PLASTICIZERS AND GEL COATS

For many plasticizer and polyester gel coat applications, it has been established that the theoretical dosage level of the appropriate Solplus™ or Solsperse™ hyperdispersant in a pigment dispersion equates to 2 mg of Solplus™ or Solsperse™ polymeric hyperdispersant/square meter of pigment surface area.

This can be expressed as % Agent On the Weight of Pigment (% AOWP).

$$\% \text{ AOWP} = \frac{\text{pigment surface area (m}^2\text{/g)}}{5}$$

THERMOSET COMPOSITES

For thermoset composite applications, testing has confirmed a loading of between 0.5% and 2% of the appropriate Solplus™ hyperdispersant on the weight of filler is effective.

Minor adjustments may, however, be required depending on the specific grade of filler used.

METHOD OF USE/ORDER OF ADDITION – PLASTIC APPLICATIONS

MASTERBATCH/COMPOUND

1. Charge polymer to pre-blending equipment.
2. Add Solplus™ or Solsperse™ agent and blend thoroughly with the polymer to coat the surface of the polymer.
3. Add pigments, fillers, processing aids and other essential ingredients and continue pre-blending.
4. Process the resultant blend in normal manner (extrusion, internal mixer, 2-roll mill, etc.).

It is essential to follow this order of addition carefully since it allows for maximum distribution of the Solplus™ or Solsperse™ additive and produces intimate contact between the hyperdispersant and the polymer. This intimate contact gives the best results.

PLASTICIZERS, GEL COATS AND THERMOSET COMPOSITES

1. Dissolve the appropriate Solsperse™ or Solplus™ hyperdispersant in the millbase plasticizer or resin.
2. If required, add a synergist and distribute evenly with stirring (note: the synergist is virtually insoluble).
3. Add the pigment or filler in stages and disperse in normal manner.



HYPERDISPERSANTS FOR THERMOPLASTICS AND THERMOSETS – PRODUCT LIST

PRODUCT NAME	PHYSICAL DESCRIPTION	PACKAGE SIZE (kg)	% ACTIVE CONTENT	SOLVENT/ CARRIER	SUITABLE APPLICATION(S)
Solplus™ D510	Yellow viscous liquid	D20/D180	100	–	Thermoset composites, pigmented gel coats
Solplus™ D520	Straw colored viscous liquid	P25/P200	100	–	Thermoset composites
Solplus™ D540	Pale amber to brown viscous liquid	P20/P200	100	–	Thermoset composites
Solplus™ D541	Amber liquid	D25, D180	100	–	Thermoset composites
Solplus™ D545	Pale amber to brown viscous liquid	P25, P200, I1000	100		Thermoset composites
Solplus™ D560	Pale yellow liquid	P20/P180	100	–	Thermoset composites
Solplus™ D570	Colorless to brown viscous liquid	P25, P200	100		Thermoset composites
Solplus™ D610	Yellow viscous liquid	P20, D180	100	–	Thermoset composites and gelcoats, polyester polyols
Solplus™ DP310*	Off white powder	B825	100	–	Masterbatch/compounding
Solplus™ DP700	Brown liquid	D20, D180, I750	100	–	Plasticizers
Solplus™ ES1000	White to off-white liquid	D20, D160	10	Hydrocarbon carrier	Thermoset composites (styrene suppressant)
Solplus™ K200*	Pale yellow to brown viscous liquid	D20/D180	50	DOA (Diocyladipate)	Plasticizers and liquid colors for plastics
Solplus™ K210	Pale yellow to brown viscous liquid	D20/D180	50	DINP (Diisononylphthalate)	Plasticizers and liquid colors for plastics
Solplus™ K220	Amber to brown viscous liquid	D20/D180/I940	100	–	Plasticizer and liquid colors for TP and PVC
Solplus™ K240*	Pale yellow to brown viscous liquid	D20, D150	100		Liquid colors for plastics

PRODUCT NAME	PHYSICAL DESCRIPTION	PACKAGE SIZE (kg)	% ACTIVE CONTENT	SOLVENT/ CARRIER	SUITABLE APPLICATION(S)
Solplus™ K241*	Pale yellow to brown viscous liquid	D20, D150	50	FDA compliant natural oil	Liquid colors for plastics
Solplus™ K251*	Pale yellow to brown viscous liquid	D20, D150	50	FDA compliant natural oil	Liquid colors for plastics
Solplus™ K500	Pale yellow to brown viscous liquid	D20/D180/I900	100	–	Plasticizers
Solplus™ R700	Yellow viscous liquid	D20/D180	100	–	Polyether or polyester polyols
Solplus™ R710	Pale to dark amber liquid	D20, D180	100	–	Polyether or polyester polyols
Solplus™ R720	Amber liquid	D25/D190/I1000	100	–	Polyether or polyester polyol
Solplus™ R730	Pale yellow to amber viscous liquid	D25/D180/I1000	100	–	Polyether or polyester polyol
Solplus™ TX5	Pale yellow liquid	D25, D200	40	MPA	Thermoset composites (silica replacement)
Solperse™ 3000*	Waxy paste/ viscous liquid	D20/D170	100	–	Plasticizers
Solperse™ 5000S	Blue powder	B15	100	–	Synergist
Solperse™ 11000*	Amber liquid	D20/D180	50	Mineral oil	Plasticizers and liquid colors for plastics
Solperse™ 12000S	Blue powder	B25	100	–	Synergist
Solperse™ 13650	Amber liquid	D20/D150	50	Diundecyl-phthalate	Plasticizers
Solperse™ 21000*	Waxy paste/ viscous liquid	D20/D170	100	–	MBX/compound
Solperse™ 22000	Yellow powder	B20	100	–	Synergist

KEY: Packaging: B = box, D = drum, I = IBC, P = plastic drum

*Approved for food contact. Some limitations apply. Please consult your regional Lubrizol sales office.



NORTH AMERICA

Lubrizol Advanced Materials, Inc.
9911 Brecksville Road
Brecksville, OH 44141 USA
+1.800.380.5397

EUROPE

Lubrizol Deutschland GmbH
Max-Planck-Str. 6
27721 Ritterhude Germany
+49.421.69333

ASIA-PACIFIC

Lubrizol Specialty Chemicals
(Shanghai) Co., Ltd
10/F, Park Center International
No. 1088 Fang Dian Road
Shanghai 201204, PR China
+8621.3866.0366

SOUTH AMERICA

Lubrizol do Brasil Aditivos Ltda
Avenida Nove de Julho, 3653
Jardim Paulista
Sao Paulo – SP
01407-000
+55.11.4097.0250

Visit us at:
www.lubrizol.com/plastics

WHAT WE ADD MAKES THE DIFFERENCE.™

Lubrizol is a market-driven innovator of specialty chemicals that solve today's challenges in the paints and coatings, printing and packaging, paper and textiles, plastics and composites and digital print markets. More than just a supplier, we are a collaborator with extensive experience in surface protection, dispersion, adhesion and barrier properties that enables us to enhance the performance, simplicity and sustainability benefits of our customers' products. With a commitment to collaboration, applied science, and demonstrated value, our team of experts is dedicated to exceeding customer expectations for both the simplest and toughest requirements. Count on Lubrizol to make the difference.



The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

Trademarks owned by The Lubrizol Corporation or its affiliates.
©The Lubrizol Corporation 2020, All Rights Reserved.