



PTFE-FREE WAX ADDITIVES FOR INKS AND COATINGS

DON'T SACRIFICE ON PERFORMANCE!

Lubrizol has developed a range of PTFE-free micronized waxes and liquid wax dispersions for water-based and solvent-based inks and coatings that significantly improve rub, scratch and abrasion resistance while reducing coefficient of friction (COF) comparable to traditional PTFE-based wax additives.

Benefits

- Highly effective surface protection
- Suitable for use in water-based and solvent-based inks & coatings
- Small particle size and narrow particle size distribution
- Excellent slip/COF reduction
- Rub, scratch and mar resistance
- Anti-blocking
- Gloss retention
- EU 10/2011 and FDA 21 CFR 175.300 Compliant

Benefits of PTFE

Polytetrafluoroethylene (PTFE) has brought desirable properties for traditional ink and coating applications. Low molecular weight PTFE micronized powders have been used to reduce the coefficient of friction of the film to aid mobility and to lubricate and protect surfaces from scratch and abrasion forces. Anti-blocking properties and release effects can also be generated.

Achieving low molecular weight and friability has typically required irradiation to enable particle size reduction using conventional micronization techniques. The irradiation process has been demonstrated to generate PFAS components, with PFOA and PFOS both classified as reproductive toxins and suspected carcinogens.

Regulatory Actions Impacting the use of PTFE

In 2019, a global ban on PFOA and its salts as persistent organic pollutants (POPs) was agreed under the Stockholm Convention restricting the use of raw materials containing >25 ppb PFOA. Following the legislation, certain PTFE raw materials were withdrawn. This global impact is driving the ink and coating industries to shift away from raw materials like PTFE. Additionally, PTFE stability properties that have driven use in many applications and its halogen content also impact cradle-to-cradle policies.

Lubrizol's Solutions

Lubrizol's technical team has focused on development of PTFE-alternative wax additives to deliver similar properties to PTFE-containing additives. PTFE-alternative technologies are available in micronized and dispersed forms of surface modifying additives under the Lanco™ wax additives brand. More products are currently under development to meet specific customer needs and to provide additives for a wider range of applications.

Lubrizol Locations

NORTH AMERICA

Lubrizol Advanced Materials, Inc.
9911 Brecksville Road
Brecksville, OH 44141 USA
+1.888.234.2436

EUROPE

Lubrizol Deutschland GmbH
Max-Planck-Str. 6
27721 Ritterhude Germany
+49.421.69333

ASIA-PACIFIC

Lubrizol Specialty Chemicals
(Shanghai) Co., Ltd
10/F, Park Center International
No. 1088 Fang Dian Road
Shanghai 201204, PR China
+8621.3866.0366

SOUTH AMERICA

Lubrizol do Brasil Aditivos Ltda
Avenida Nove de Julho, 3653
Jardim Paulista
Sao Paulo – SP
01407-000
+55.11.4097.0250

Micronized PTFE-Free Wax Additives

Product Name	Polymer Type	Particle Size		Melting Point °C (°F)	Density at 20°C g/cm ³	Applications			
		Dv50 µm	Dv90 µm			Can Coatings	Coil & General Industrial Coatings	Wood Coatings	Inks
Lanco™ 1510 SF	Modified Polyolefin Wax	≤6	≤14	106 (223)	0.96	•	•	•	•
Lanco™ 1510 EF	Modified Polyolefin Wax	≤5	≤9.5	106 (223)	0.96	•	• (thin film)		•
Lanco™ 2510 SF	Inorganically Modified Wax Compound	≤6	≤14	105 (221)	1.05	•	•	•	•
Lanco™ 2520 SF	Inorganically Modified Wax Compound	≤6	≤14	105 (221)	1.07	•	•	•	•
Lanco™ 2520 EF	Inorganically Modified Wax Compound	≤5	≤10	105 (221)	1.07	•	• (thin film)	•	•
Lanco™ 2530 EF	Organically Modified Wax Compound	≤6	≤12	116 (241)	0.92	• (thin film)	•		•
Lanco™ 2540 SF	Organically Modified Wax Compound	≤6	≤14	128 (262)	0.85	•	•	•	•
Lanco™ 2541 SF	Organically Modified Wax Compound	≤6	≤14	144 (291)	0.83	•	•	•	•

Dispersed PTFE-Free Wax Additives

Product Name	Polymer Type	Solids %	Solvent	Particle Size		Melting Point °C (°F)	Density at 20°C g/cm ³	Applications		
				Dv50 µm	Dv90 µm			Can Coatings	Coil & General Industrial Coatings	Wood Coatings
Lanco™ Glidd 6635	Wax Combination	30	Water, Butyl Glycol	≤6	≤12	124	0.96	•	•	•
Lanco™ Glidd 6692	Wax Combination	29	Water, Butyl Glycol	≤3	≤7	86	0.98	• (thin film)	•	•
Lanco™ Glidd 7605	Inorganically Modified Polyolefin Wax	20	Aromatic 100, Butyl Glycol	≤4	≤8	105 (221)	0.93	• (thin film)		
Lanco™ Glidd 7607	Inorganically Modified Polyolefin Wax	20	Water, Butyl Glycol	≤4	≤8	105 (221)	0.99	• (thin film)	•	•
Lanco™ Glidd 7610	Inorganically Modified Polyolefin Wax	18.5	Butyl Glycol	≤4	≤8	82 (180)	0.93	• (thin film)	•	•
Lanco™ Glidd 7612	Inorganically Modified Polyolefin Wax	27	Water, Butyl Glycol	≤6	≤12	106 (223)	0.98	•	•	•
Lanco™ Glidd 7678	Modified Polyolefin Wax	20	Butyl Glycol	≤3.5	≤7	104	0.9	• (thin film)	•	•



Performance Coatings

Lubrizol Advanced Materials, Inc. ("Lubrizol") hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.