



RESINS PRODUCT GUIDE FOR PAINTS & COATINGS

Lubrizol

Performance Coatings

www.lubrizol.com/coatings



ENABLING CUSTOMER SUCCESS



Industry Knowledge

With an experienced team of coating, ink, and composite specialists, Lubrizol is dedicated to close collaboration with customers and industry experts to gain and share industry knowledge, insights, and solutions.

Technical Support

Lubrizol staffs fully-equipped labs in Europe, North America, Latin America and Asia to bring regional formulation capabilities and support to customers, wherever they are in the world.

Quality

From product development to production and distribution, we carefully control all processes to ensure the quality of our products and to enable customers to gain a competitive edge.

Innovative Solutions

Lubrizol invests in market-driven innovation to address relevant and timely coatings challenges and opportunities for customers.

On-Time Delivery

Product availability and on-time delivery are vital to any business. To answer these needs, Lubrizol has a worldwide network of distribution points. This comprehensive network provides immediate access to customer service.



Wood Coatings

Lubrizol has the key ingredients to improve many wood coating formulations. With a wide variety of resin technologies for residential and commercial applications, we help formulators meet performance and aesthetic preferences while maintaining regulatory requirements and sustainability targets.

Building & Construction Coatings

Lubrizol specialty chemical solutions deliver value for coatings manufacturers, architects, builders, and building owners. Our advanced portfolio of resins and polymers are commonly used in masonry coating, concrete coating, elastomeric coating, liquid roof coating, mortar modification and other building and construction coating products to beautify and strengthen a diverse range of interior and exterior surfaces. With advanced Lubrizol technologies, formulators can improve coating performance and production efficiency. Contractors and architects can shorten construction schedules and reduce labor costs. Property owners will enjoy long-lasting, visually appealing surfaces.

Industrial Coatings

Lubrizol innovates technologies for a variety of industrial metal coating applications. Our resin technologies enhance key performance attributes, imparting superior corrosion resistance, scratch and mar resistance and improved overall performance. Lubrizol offers primer, topcoat and direct-to-metal resin technologies that offer a superior balance of durability and gloss.

Transportation Coatings

Lubrizol innovates cutting-edge chemical solutions for automotive OEM and vehicle refinish applications, such as interior, exterior and underbody coating technologies. We address the challenges that face coating manufacturers, automotive manufacturers and consumers, providing customized solutions and value-added, long-lasting coatings. Our technologies help formulators meet the functionality needs of the most demanding transportation coatings.

Wood Coating Technologies

Acrylic Technologies for Wood Coatings		
Lubrizon Product	Polymer Type	Key Benefits
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	Low VOC exceptional chemical & block resistance, early hardness & external durability also suitable for use in eco-label paints & coatings.
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	Early hardness, sandability with superior chemical resistance; blend vehicle with polyurethanes
Carbaset® 7722	Acrylic Emulsion	Low VOC, adhesion, stain blocking, & scrub resistance in all sheens
Carbaset® 7733	Acrylic Emulsion	Low VOC, exterior durability & scrub resistance in high gloss formulations
Carbaset® AMO 400	Acrylic Oil Modified Copolymer	Renewable, low VOC, high melt temperature for high speed sanding, improved toughness, black heel mark & abrasion resistance; blend vehicle with other resins
Carbaset® CR 726	Self-crosslinking Acrylic Emulsion	Low VOC & excellent hardness
Carbaset® CR 7181	Self-crosslinking Acrylic Emulsion	Hard, excellent chemical resistance, air & forced dry compatible; adhesion to wood, metal & plastic
Carbaset® 3142	Styrene Acrylic Emulsion	Low VOC, high gloss, exceptional block & chemical resistance, multi-substrate adhesion, exterior durability; alkyd-like application
Carbaset® CA 7147	Acrylic Emulsion	High gloss, fine particle size, fast drying, non-yellowing, water, weather, & dirt pick-up resistant

*Produced in multiple facilities; product name may vary

Polyurethane Dispersion Technologies for Wood Coatings		
Lubrizon Product	Polymer Type	Key Benefits
Aptalon™ W8060	Self-crosslinking Polyurethane Dispersion - Polyamide	Renewable, superior chemical resistance, balance of hardness, abrasion & scratch resistance
Aptalon™ W8062	Self-crosslinking Polyurethane Dispersion - Polyamide	Renewable, lower VOC, improved scuff & black heel mark resistance
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	Low gloss without matting agents & excellent abrasion resistance
Aptalon™ 8080HS	High-solids Polyurethane Dispersion - Polyamide	Renewable, rapid hardness development, excellent chemical, mar & scuff resistance, crosslinkable
Sancure™ 970	Polyurethane Dispersion - Polyester	Adhesion to multiple substrates, excellent hardness & chemical resistance, crosslinkable
Turboset™ 2027	Self-crosslinking Polyurethane Dispersion - Polyester	Excellent chemical & stain resistance
Turboset™ Ultra Eco	Self-crosslinking Polyurethane Dispersion - Polyether	Low VOC, superior black heel mark resistance, excellent hardness & chemical resistance
Sancure™ AU 4050	Self-crosslinking Acrylic/Polyester Polyurethane Hybrid Dispersion	Non-yellowing, excellent chemical, abrasion & scuff resistance

Lubrizon Product	Applications						MFFT (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	Floors	Cabinets	Furniture	Windows & Doors	Interior Trims & Primers	Stains						
Carbaset® 2951		•	•	•	•	•	<5	44	43	8	30 - 250	1.01
Carbaset® 2968	•	•	•				57	41.5	39	7.5	10 - 300	1.04
Carbaset® 7722					•		<5	50	48	8.4	40 - 800	1.06
Carbaset® 7733					•		21	50	46	8.4	40 - 800	1.06
Carbaset® AMO 400	•	•	•	•	•	•	12	40	37.5	7.5	<500	1.06
Carbaset® CR 726	•	•	•	•			35	42	41	8	50 - 600	1.05
Carbaset® CR 7181		•	•				90	42	39.1	9	50	1.06
Carbaset® 3142			•	•	•		7	41	40	7	10-500	1.02
Carbaset® CA 7147					•	•	6	46	45	8.5	300 - 1200	1.01

Lubrizon Product	Applications						MFFT (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	Floors	Cabinets	Furniture	Windows & Doors	Interior Trims & Primers	Stains						
Aptalon™ W8060	•		•				59	36	33	7.5	<500	1.05
Aptalon™ W8062	•	•	•				31	36	33	7.5	<500	1.04
Aptalon™ W8030	•	•	•				61	35	34.2	7.5	<500	1.04
Aptalon™ 8080HS	•		•	•			45	50	50	7.5	<500	1.05
Sancure™ 970	•		•	•			50	42	41	8	<500	1.06
Turboset™ 2027	•		•				22.5	40	35	8	<500	1.07
Turboset™ Ultra Eco	•		•				<5	36	35	7.5	<400	1.04
Sancure™ AU 4050	•		•	•			15	36	32	8	<125	1.05

Building & Construction Coating Technologies

Acrylic Technologies for Building & Construction Coatings		
Lubrizol Product	Polymer Type	Key Benefits
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	Low VOC, Exceptional chemical & block resistance & early hardness
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	Robust water resistance, high hardness, outstanding gloss/wet look, excellent chemical & mar resistance
Carbaset® 7722	Acrylic Emulsion	Low VOC, good scrub resistance, early block & print resistance, pigmentable
Carbaset® 7733	Acrylic Emulsion	Low VOC, high gloss, inherent stain removal & washability, early block resistance & great flow & leveling
Carbaset® AE 960*	Acrylic Emulsion	Low VOC, excellent dirt pick-up, balance of elongation & tensile strength, outstanding water resistance, weathering & crack bridging also suitable for ASTM D6083 compliant paints & coatings.
Carbaset® CA 7147	Acrylic Emulsion	Low VOC, small particle size, alkali resistance, high water vapor permeability & low CO ₂ permeability
Carbaset® CA 7107	Acrylic Emulsion	Low VOC, excellent water, alkali & weathering resistance
Carbaset® CA 7100RC	Styrene Acrylic Emulsion	Low VOC, balance of mechanical properties, excellent adhesion to most masonry substrates at high PVC loading, water & alkali resistance
Carbaset® CA 7160RC	Styrene Acrylic Emulsion	Low VOC, alkali resistant, excellent adhesion to most masonry substrates at high PVC loading
Carbaset® CA 7120RC	Styrene Acrylic Emulsion	Low VOC, excellent water, alkali & dirt pick-up resistance, balance of elasticity & tensile strength. Great adhesion to most masonry substrates including terracotta tiles.
Carbaset® CR 7185	Acrylic Emulsion	Excellent water retention, concrete curing properties & high alkali resistance
Carbaset® CA 600*	Acrylic Emulsion	Early water resistance, fast drying, great substrate penetration, alkaline, blushing, efflorescence, chemical resistance, non-yellowing & exterior exposure
Carbaset® CA 1009*	Acrylic-Polyurethane Polymer	Low VOC, minimal water uptake & capillary absorption, superior water & bituman bleed through resistance, excellent exterior durability & heat stable.
Carbaset® RPT 2000A	Acrylic Copolymer Emulsion	Low VOC, superior adhesion to wide range of substrates & great bitumen bleed through resistance
Carbaset® RPT 3030	Acrylic Emulsion	Low VOC, excellent low temperature elasticity, ASTM D6083 compliance capable, & adhesion to EPDM
Carbaset® SA 850*	Acrylic Copolymer Emulsion	Low VOC, robust crack-bridging performance & weatherability, resistant to chalking, fading, & water penetration, excellent dirt pick-up, efflorescence, alkali properties
Carbaset® 3142	Styrene Acrylic Emulsion	Low VOC, high gloss coatings, exterior durability, good block & stain resistance, multi-substrate adhesion; alkyd-like application
Carbaset® X-Flex 100	High Solids Acrylic Emulsion	Low VOC, highly elastic cement compatible binder, excellent alkali & water resistance
Carbaset® XM200	Acrylic Emulsion	Low VOC, cement compatible binder, enhances adhesion & mechanical properties of cementitious formulations
Carbaset® PL 958*	Acrylic Emulsion	Low VOC, high tensile strength for clear & pigmented temporary protection & excellent chemical resistance. Peelable coatings.
Carbotac® 1811	Acrylic Emulsion	Low VOC, long open time polymer for bonding bridge masonry applications

*Produced in multiple facilities; product name may vary

Lubrizol Product	Applications				MFFT (°C)	TG (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	Liquid Roof	Vertical Masonry	Horizontal Masonry	Mortar Modifier							
Carbaset® 2951		•	•		<5		44	43	8	30 - 250	1.01
Carbaset® 2968			•		57		41.5	39	7.5	10 - 300	1.04
Carbaset® 7722		•	•		<5		50	48	8.4	40 - 800	1.06
Carbaset® 7733		•	•		21		50	46	8.4	40 - 800	1.06
Carbaset® AE 960*	•	•			<5	-25	56	55	8.2	<2000	1.02
Carbaset® CA 7147		•	•		6		47	46	8.8	300-1200	1.01
Carbaset® CA 7107	•	•			0	8	50	47	8.5	9000	1.05
Carbaset® CA 7100RC	•	•			0	-10	50	49	8.3	8.000-11000	1.01
Carbaset® CA 7160RC		•	•		21	18	50	49	8.3	2500-5000	1.01
Carbaset® CA 7120RC	•	•			0	0	48	47	8.3	8000-12500	1.01
Carbaset® CR 7185			•		44		42	41	8.5	10-300	1.03
Carbaset® CA 600*			•		35	55	42	41	8.3	41	1.06
Carbaset® CA 1009*	•	•			2	5	55	53	8	150 - 800	1.1
Carbaset® RPT 2000A	•				<5	10	55	53	8.5	100 - 15000	1.04
Carbaset® RPT 3030	•	•			0	-35	55	53	8	200-1200	1.06
Carbaset® SA 850*	•	•			<5	10	55	53	8.5	100 - 15000	1.04
Carbaset® 3142		•			7		41	40	7	10-500	1.02
Carbaset® X-Flex 100				•		-40	60	60	8.5	100-1000	1.01
Carbaset® XM200				•	0	19	48.5	48	8.5	25	1.01
Carbaset® PL 958*					0		46.8	43	8	40-125	1.07
Carbotac® 1811					0	-43	55	53	3.5	120	1.03

Building & Construction Coating Technologies

Polyurethane Dispersion Technologies for Building & Construction Coatings		
Lubrizon Product	Polymer Type	Key Benefits
Aptalon™ 8080HS	High-solids Polyurethane Dispersion - Polyamide	Renewable, rapid hardness, excellent chemical, mar & scuff resistance
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	Low gloss without matting agents & excellent abrasion resistance
Aptalon™ W8060	Self-crosslinking Polyurethane Dispersion - Polyamide	Renewable, superior chemical resistance, balance of hardness & abrasion resistance & scratch resistance
Aptalon™ W8062	Self-crosslinking Polyurethane Dispersion - Polyamide	Lower VOC, improved scuff & black heel mark resistance
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance
Sancure™ 20041	Polyurethane Dispersion - Polyester	Cosolvent-free, excellent hardness, compatible with acrylics; crosslinkable
Sancure™ 861	Polyurethane Dispersion - Polyether	Low VOC, cosolvent-free, hydrolytic & aging stability, alkali, abrasion & chemical resistance
Sancure™ 20025F	Aliphatic Polyurethane Dispersion - Polyester	Low VOC, provides enhanced durability when blended with acrylics
Sancure™ 970	High Solids Polyurethane Dispersion - Polyester	Chemical & abrasion resistance; crosslinkable
Sancure™ AU4050	Self-crosslinking Acrylic/ Polyester Polyurethane Hybrid Dispersion	Non-yellowing, excellent chemical, abrasion & scuff resistance
Turboset™ Ultra Eco	Self-crosslinking Polyurethane Dispersion - Polyether	Low VOC, superior black heel mark resistance, excellent hardness & chemical resistance
Turboset™ 2027	Self-crosslinking Polyurethane Dispersion - Polyester	Cosolvent-free, excellent chemical resistance & durability

Solution Acrylic Technologies for Building & Construction Coatings		
Lubrizon Product	Polymer Type	Key Benefits
Doresco® L91-1X	Solvent-borne Acrylic Polymer in Xylene	Hard solvent-borne acrylic designed for general purpose concrete coating
Doresco® M6A	Solvent-borne Thermoplastic Acrylic in Xylene	Exterior durability & adhesion to multiple substrates
Doresco® T6T	Solvent-borne Thermoplastic Acrylic in Toluene	Quick drying road-markings for high traffic areas
Doresco® T5T60	Solvent-borne Thermoplastic Acrylic in Toluene	Quick drying road-marking for medium traffic areas; internally plasticized version of Doresco T6T

Polyurethane Dispersion Technologies for Building & Construction Coatings									
Lubrizon Product	Applications			MFFT (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	Liquid Roof	Vertical Masonry	Horizontal Masonry						
Aptalon™ 8080HS			•	45	50	50	7.5	<500	1.05
Aptalon™ W8030			•	5	35	33	8	<500	1.03
Aptalon™ W8060			•	59	36	33	7.5	<500	1.05
Aptalon™ W8062			•	31	36	33	7.5	<500	1.04
Aptalon™ M8100			•	58	37	34	7.5	<500	1.04
Sancure™ 20041	•		•	22	34	30	8	150	1.05
Sancure™ 861	•	•		<5	40	39	7.5	<90	1.02
Sancure™ 20025F	•	•		<5	48	45	8	<500	1.05
Sancure™ 970			•	50	42	41	8	<500	1.06
Sancure™ AU4050			•	15	36	32	8	<125	1.05
Turboset™ Ultra Eco			•	<5	36	35	7.5	<400	1.04
Turboset™ 2027			•	22.5	40	35	8.7	<500	1.07

Solution Acrylic Technologies for Building & Construction Coatings									
Lubrizon Product	Applications			Solvent	Acid Number	TG (°C)	% Weight Solids	Viscosity (CPS)	Specific Gravity
	Liquid Roof	Vertical Masonry	Horizontal Masonry						
Doresco® L91-1X		•		Xylene	<10	57	49	5000 - 8000	1.05
Doresco® M6A	•	•	•	Xylene	<10	61	50	5.7	1.03
Doresco® T6T			•	Toluene	<10	61	50	3700	
Doresco® T5T60			•	Toluene	<10	43	60	7000	1.07

Industrial Coating Technologies

Acrylic & PVDC Technologies for Industrial Coatings		
Lubrizol Product	Polymer Type	Key Benefits
Carbaset® 514*	Alkali Strippable Acrylic Dispersion	High gloss, fast drying, excellent hardness & adhesion
Carbaset® 560	Alkali Strippable Acrylic Dispersion	Water & UV resistance, excellent mechanical stability & adhesion
Carbaset® 441	Peelable Acrylic Emulsion	Balance of adhesion & cohesion for strippability, excellent toughness & durability
Carbaset® CR 3090*	Styrene Acrylic Emulsion	Great corrosion & weathering resistance; adhesion to CRS, Phosphated & galvanized steel
Carbaset® CR 3100	Styrene Acrylic Emulsion	Low VOC, great corrosion & weathering resistance; adhesion to CRS, HRS & galvanized steel
Carbaset® CR 7185	Acrylic Emulsion	Fast dry, resistant to gas, solvents, impact, water & humidity; adhesion to phosphated & stainless steel
Carbaset® CR 765*	Styrene Acrylic Emulsion	Balance of performance properties, high gloss, water & humidity resistance, reactive pigment stability; adhesion to CRS, Phosphated, aluminum, copper, stainless steel
Carbaset® PL 3127	Peelable Acrylic Copolymer Emulsion	Low VOC, fast drying, & corrosion resistance
Carbaset® PL 958*	Peelable Acrylic Copolymer Emulsion	Low VOC, high elasticity, solvent & breaking resistance
Carbaset® CR 7162E	Styrene Acrylic Emulsion	Air & force dry, gloss & semi-gloss, corrosion & humidity resistance; adhesion to plastic, metal & masonry
Carbaset® 3142	Styrene Acrylic Emulsion	Gloss & semi-gloss, wet adhesion, block & sag resistance, interior & exterior architectural; alkyd like application
Permax™ 805	PVDC Emulsion	Low VOC, humidity resistant, increased shelf-life & in-can stability; adhesion to aluminum, CRS, Bonderite 1000, ground & galvanized steel
Permax™ 805B	PVDC Emulsion	Low VOC, small particle size, low MVTR, excellent corrosion resistance & durability, adhesion to aluminum, CRS, ground & galvanized steel, potable water applications*

*Produced in multiple facilities; product name may vary

Polyurethane Technologies for Industrial Coatings		
Lubrizol Product	Polymer Type	Key Benefits
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance
Aptalon™ M8120	Self-crosslinking Polyurethane Dispersion - Polyamide	Excellent adhesion to metal surfaces, extraordinary hardness and durability in a 1k WB DTM, outstanding chemical & corrosion resistance.
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	Low gloss without matting agents & excellent abrasion resistance
Sancure™ 970	Polyurethane Composite - Polyester	Great chemical, abrasion, & alkali resistance, crosslinkable; adhesion to ferrous & non-ferrous metals

*Produced in multiple facilities; product name may vary

Applications											
Lubrizol Product	DTM	Primer	Topcoat	Temporary Coating	MFFT (°C)	TG (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
Carbaset® 514*				•	10	28	40	38	6.6	100 - 500	1.05
Carbaset® 560				•	17	47	27	24.5	7.6	<200	1.03
Carbaset® 441				•	18	23	45	42	8	100	1.04
Carbaset® CR 3090*	•	•	•		33	37	45	42	8.5	<500	1.05
Carbaset® CR 3100	•	•	•		9	28	43.5	41	8	<500	1.05
Carbaset® CR 7185	•	•	•		40		42	40	8.3	5-120	1.03
Carbaset® CR 765*	•	•	•		34		41	40.7	8	10 - 150	1.03
Carbaset® PL 3127				•	5	15	44	42.8	7.8	150	1.05
Carbaset® PL 958*				•	<3		46	43.4	7	40 - 125	1.07
Carbaset® CR 7162E	•	•	•		23		41.5	39	8	10-100	1.03
Carbaset® 3142	•	•	•		7		41.5	40	8.5	10-500	1.02
Permax™ 805	•	•			13.5		60	50.4	1.0 - 2.2	85	1.28
Permax™ 805B	•	•			13.5		60	50	1.8	85	1.28

Applications										
Lubrizol Product	DTM	Primer	Topcoat	MFFT (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity	
Aptalon™ M8100			•	58	37	34	8	<500	1.04	
Aptalon™ M8120	•	•	•	50	37	34	8.5	<500	1.09	
Aptalon™ W8030			•	61	35	34.2	7.5	<500	1.04	
Sancure™ 970	•	•	•	50	42	41	8	<500	1.06	



Industrial Coating Technologies

Solution Acrylic Technologies for Industrial Coatings		
Lubrizol Product	Polymer Type	Key Benefits
Carbaset® 514*	Alkali Strippable Acrylic Dispersion	High gloss, fast drying, excellent hardness & adhesion
Carbaset® 560	Alkali Strippable Acrylic Dispersion	Water & UV resistance, excellent mechanical stability & adhesion
Carbaset® 441	Peelable Acrylic Emulsion	Balance of adhesion & cohesion for strippability, excellent toughness & durability
Carbaset® CR 3090*	Stryrene Acrylic Emulsion	Great corrosion & weathering resistance; adhesion to CRS, Phasphated & galvanized steel
Carbaset® CR 3100	Stryrene Acrylic Emulsion	Low VOC, great corrosion & weathering resistance; adhesion to CRS, HRS & galvanized steel
Permax™ 805B	PVDC Emulsion	Low VOC, small particle size, low MVTR, excellent corrosion resistance & durability, adhesion to aluminum, CRS, ground & galvanized steel, potable water applications*

Lubrizol Product	Applications				MFFT (°C)	TG (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	DTM	Primer	Topcoat	Temporary Coating							
Carbaset® 514*				•	10	28	40	38	6.6	100 - 500	1.05
Carbaset® 560				•	17	47	27	24.5	7.6	<200	1.03
Carbaset® 441				•	18	23	45	42	8	100	1.04
Carbaset® CR 3090*	•	•	•		33	37	45	42	8.5	<500	1.05
Carbaset® CR 3100	•	•	•		9	28	43.5	41	8	<500	1.05
Permax™ 805B	•	•			13.5		60	50	1.8	85	1.28

Transportation Coating Technologies

Resin Technologies for Transportation Coatings		
Lubrizol Product	Polymer Type	Key Benefits
Acrylic Technologies		
Carbaset® CR 7181	Self-crosslinking Acrylic Emulsion	High gloss, excellent UV resistance; adhesion to a variety of plastics including ABS, Lexan, Melamine, & Noryl
Carbaset® PC 27	Self-crosslinking Acrylic Emulsion	Superior chemical resistance to sunscreens, insect repellents, surface cleaners & protectants, excellent scratch, abrasion & print resistance; adhesion to a to a variety of plastics including ABS, Lexan, Noryl
Polyurethane Technologies		
Sancure™ 20025F	Aliphatic Polyurethane Dispersion - Polyester	Low VOC, durable, elastic, crosslinkable; adhesion to nylon & polyester, heat sealable
Sancure™ PC 55	Aliphatic Polyurethane Dispersion - Polyester/ Polycarbonate	Low VOC, balance of mar resistance with soft tactile feel, superior chemical resistance to sunscreens, insect repellents, surface cleaners & protectants, & excellent UV resistance
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance

Lubrizol Product	Applications		MFFT (°C)	% Weight Solids	% Volume Solids	pH	Viscosity (CPS)	Specific Gravity
	Primer	Topcoat						
Acrylic Technologies								
Carbaset® CR 7181	•	•	90	42	39	9	6 - 50	1.06
Carbaset® PC 27	•	•	90	42	40	8.5	50 - 200	1.05
Polyurethane Technologies								
Sancure™ 20025F		•	<5	48	45	8	<500	1.05
Sancure™ PC 55		•	<5	42	39	7	<500	1.05
Aptalon™ M8100		•	58	37	34	7.5	1.05	1.04

Acrylic/PVDC Technologies						
Lubrizon Product	Polymer Type	% Weight Solids	MFFT (°C)	APEO-Free ¹	Formaldehyde-Free ¹	Availability ²
Acrylic Technologies						
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	44	<5	Yes	Yes	NA EMEAI
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	41.5	57	Yes	Yes	NA EMEAI
Carbaset® 3142	Styrene Acrylic Emulsion	41	7	Yes	Yes	EMEAI
Carbaset® 441	Peelable Acrylic Emulsion	45	18	Yes	No	NA
Carbaset® 514	Alkali Strippable Acrylic Emulsion	40	10	Yes	Yes	NA EMEAI
Carbaset® 560	Alkali Strippable Acrylic Emulsion	27	17	Yes	Yes	NA EMEAI
Carbaset® 7722	Acrylic Emulsion	50	<5	Yes	No	NA EMEAI
Carbaset® 7733	Acrylic Emulsion	50	21	Yes	No	NA EMEAI
Carbaset® AE 960 ³	Acrylic Emulsion	56	<5	Yes	Yes	NA EMEAI
Carbaset® AMO 400	Acrylic Oil Modified Copolymer	40	12	Yes	Yes	NA EMEAI
Carbaset® CA 1009 ³	Acrylic-Polyurethane Polymer	55	2	Yes	Yes	NA EMEAI
Carbaset® CA 600 ³	Acrylic Emulsion	42	35	Yes	Yes	NA EMEAI
Carbaset® CA 7100RC	Styrene Acrylic Emulsion	48	0	Yes	Yes	EMEAI
Carbaset® CA 7107	Acrylic Emulsion	50	0	Yes	No	EMEAI
Carbaset® CA 7120RC	Styrene Acrylic Emulsion	48	0	Yes	Yes	NA
Carbaset® CA 7147	Acrylic Emulsion	47	6	Yes	Yes	EMEAI
Carbaset® CA 7160RC	Styrene Acrylic Emulsion	50	21	Yes	Yes	EMEAI
Carbaset® CR 3090	Styrene Acrylic Emulsion	45	33	Yes	Yes	NA
Carbaset® CR 3100	Styrene Acrylic Emulsion	43.5	9	Yes	Yes	NA
Carbaset® CR 7162E	Styrene Acrylic Emulsion	41.5	23	Yes	Yes	EMEAI
Carbaset® CR 7181	Self-crosslinking Acrylic Emulsion	42	90	Yes	Yes	NA EMEAI
Carbaset® CR 7185	Acrylic Emulsion	42	40	Yes	Yes	NA EMEAI
Carbaset® CR 726	Self-crosslinking Acrylic Emulsion	42	35	Yes	Yes	NA EMEAI
Carbaset® CR 765	Styrene Acrylic Emulsion	41	34	Yes	Yes	NA EMEAI
Carbaset® PC 27	Self-crosslinking Acrylic Polymer	42	90	Yes	Yes	NA EMEAI
Carbaset® PL 3127	Peelable Acrylic Copolymer Emulsion	44	5	Yes	Yes	NA EMEAI
Carbaset® PL 958 ³	Peelable Acrylic Copolymer Emulsion	46	<3	Yes	No	NA EMEAI
Carbaset® RPT 2000 ³	Acrylic Copolymer Emulsion	55	<5	No	Yes	NA EMEAI
Carbaset® RPT 3030	Acrylic Emulsion	55	0	Yes	No	NA EMEAI
Carbaset® SA 850 ³	Acrylic Copolymer Emulsion	55	<5	No	Yes	NA EMEAI
Carbaset® X-Flex 100	High Solids Acrylic Emulsion	60	0	-	No	EMEAI
Carbaset® XM200	Acrylic Emulsion	48.5	Tg = 19	Yes	No	NA EMEAI
Carbotac® 1811	Acrylic Emulsion	55	0	Yes	No	NA EMEAI
PVDC Technologies						
Permax™ 805	PVDC Emulsion	60	13.5	Yes	Yes	NA EMEAI
Permax™ 805B	PVDC Emulsion	60	13.5	Yes	Yes	NA EMEAI

¹Ingredient not intentionally added to the composition or used in manufacture of Lubrizon product. ²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

Polyurethane Dispersion Technologies						
Lubrizon Product	Polymer Type	% Weight Solids	MFFT (°C)	APEO-Free ¹	NMP-Free ¹	Availability ²
Aptalon™ 8080HS	High-solids Polyurethane Dispersion - Polyamide	50	45	Yes	Yes	NA EMEAI
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	37	58	Yes	Yes	NA EMEAI
Aptalon™ M8120	Self-crosslinking Polyurethane Dispersion - Polyamide	37	50	Yes	Yes	NA EMEAI
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	35	61	Yes	Yes	NA EMEAI
Aptalon™ W8060	Self-Crosslinking Polyurethane Dispersion - Polyamide	36	59	Yes	Yes	NA EMEAI
Aptalon™ W8062	Self-Crosslinking Polyurethane Dispersion - Polyamide	36	31	Yes	Yes	NA EMEAI
Sancure™ 20025F	Aliphatic Polyurethane Dispersion - Polyester	48	<5	Yes	Yes	NA EMEAI
Sancure™ 20041	Polyurethane Dispersion - Polyester	34	22	Yes	Yes	NA
Sancure™ 861	Polyurethane Dispersion - Polyether	40	<5	Yes	Yes	NA EMEAI
Sancure™ 970	Polyurethane Dispersion - Polyester	50	42	Yes	Yes	NA EMEAI
Sancure™ AU4050	Self-crosslinking Acrylic/Polyester Polyurethane Hybrid Dispersion	36	15	Yes	Yes	NA EMEAI
Sancure™ PC 55	Aliphatic Polyurethane Dispersion - Polyester/Polycarbonate	42	<5	Yes	Yes	NA
Turboset™ 2027	Self-Crosslinking Polyurethane Dispersion - Polyester	40	22.5	Yes	Yes	NA EMEAI
Turboset™ Ultra Eco	Self-Crosslinking Polyurethane Dispersion - Polyether	36	<5	Yes	Yes	NA

¹Ingredient not intentionally added to the composition of Lubrizon product. ²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

Solution Acrylic Technologies					
Lubrizon Product	Polymer Type	Solvent	% Weight Solids	TG (°C)	Availability ²
Doresco® AC4-74	Solvent-borne Thermoplastic Acrylic	Toluene	45	50	NA
Doresco® CI7208	Solvent-borne Thermoplastic Acrylic	Xylene	49	39	EMEAI
Doresco® L91-1X	Solvent-borne Acrylic Polymer	Xylene	49	57	NA
Doresco® M6A	Solvent-borne Thermoplastic Acrylic	Xylene	50	61	EMEAI
Doresco® OH38	Hydroxylated Acrylics (4% OH Solids)	MPA/Xylene (1:1)	42	50	EMEAI
Doresco® OH60	Hydroxylated Acrylic (3% OH Solids)	MPA/Xylene (1:1)	50	14	NA EMEAI
Doresco® OH65	Hydroxylated Acrylic (2% OH Solids)	Xylene	50	27	NA EMEAI
Doresco® T5T60	Solvent-borne Thermoplastic Acrylic	Toluene	60	43	NA EMEAI
Doresco® T6T	Solvent-borne Thermoplastic Acrylic	Toluene	50	43	EMEAI

¹Ingredient not intentionally added to the composition of Lubrizon product. ²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

Lubrizol Locations

NORTH AMERICA

Lubrizol Advanced Materials, Inc.
9911 Brecksville Road
Brecksville, OH 44141 USA
+1.888.234.2436

EUROPE

Lubrizol Deutschland GmbH
Max-Planck-Str. 6
27721 Ritterhude Germany
+49.421.69333

ASIA-PACIFIC

Lubrizol Specialty Chemicals
(Shanghai) Co., Ltd
10/F, Park Center International
No. 1088 Fang Dian Road
Shanghai 201204, PR China
+8621.3866.0366

SOUTH AMERICA

Lubrizol do Brasil Aditivos Ltda
Avenida Nove de Julho, 3653
Jardim Paulista
Sao Paulo – SP
01407-000
+55.11.4097.0250

Lubrizol Performance Coatings is a market-driven innovator of specialty chemicals for coatings, inks and composites. Our portfolio of resin, binder, dispersant, wax additive and specialty additive technologies solves challenges across a wide range of markets and applications. Formulators choose Lubrizol to benefit from our innovative technologies, customer collaboration and global reliability. More than just a supplier, we are a valued partner with extensive experience in surface protection, dispersion, adhesion and barrier properties. We work closely with customers to enhance the performance, productivity and sustainability benefits of their products and drive new opportunities for market success.



Performance Coatings

Lubrizol Advanced Materials, Inc. ("Lubrizol") hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.