


Lubrizol

PERFORMANCE COATINGS



RESINS FOR PAINTS & COATINGS PRODUCT GUIDE



WHAT WE ADD MAKES THE DIFFERENCE.™



INDUSTRY KNOWLEDGE

Lubrizol employs experienced paint, coating, ink and plastic specialists. A constant dialogue with our customers and continuous learning enables us to understand the needs of the industry and successfully work on dynamic paint, coating and plastic needs.

TECHNICAL SUPPORT

Lubrizol staffs fully-equipped labs in Europe, North America, Latin America and Asia, all dedicated to helping our customers, answering technical questions and delivering solutions.



QUALITY PRODUCTS

From product development to production and distribution, we carefully control all processes to ensure the quality of our products and to enable customers to gain a competitive edge.

BEST SOLUTION

Lubrizol specializes in providing the right product to meet specific coating needs.



ON TIME DELIVERY

Product availability and on-time delivery are vital to any business. To answer these needs, Lubrizol has a worldwide network of distribution points. This comprehensive network provides immediate access to customer service.

WOOD COATINGS

Lubrizol has the key ingredients to improve many wood coating formulations. With a wide variety of resin technologies for residential and commercial applications, we help formulators meet performance and aesthetic preferences while maintaining regulatory requirements and sustainability targets.



BUILDING & CONSTRUCTION COATINGS

Lubrizol specialty chemical solutions deliver value for coatings manufacturers, architects, builders, and building owners. Our advanced portfolio of resins and polymers are commonly used in masonry coating, concrete coating, elastomeric coating, liquid roof coating, mortar modification and other building and construction coating products to beautify and strengthen a diverse range of interior and exterior surfaces. With advanced Lubrizol technologies, formulators can improve coating performance and production efficiency. Contractors and architects can shorten construction schedules and reduce labor costs. Property owners will enjoy long-lasting, visually appealing surfaces.

INDUSTRIAL COATINGS

Lubrizol innovates technologies for a variety of industrial metal coating applications. Our resin technologies enhance key performance attributes, imparting superior corrosion resistance, scratch and mar resistance and improved overall performance. Lubrizol offers primer, topcoat and direct-to-metal resin technologies that offer a superior balance of durability and gloss.



TRANSPORTATION COATINGS

Lubrizol innovates cutting-edge chemical solutions for automotive OEM and vehicle refinish applications, such as interior, exterior and underbody coating technologies. We address the challenges that face coating manufacturers, automotive manufacturers and consumers, providing customized solutions and value-added, long-lasting coatings. Our technologies help formulators meet the functionality needs of the most demanding transportation coatings.

ACRYLIC TECHNOLOGIES FOR WOOD COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS						MFFT (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			FLOORS	CABINETS	FURNITURE	WINDOWS & DOORS	INTERIOR TRIMS AND PRIMERS	STAINS						
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	Low VOC exceptional chemical & block resistance, early hardness & external durability also suitable for use in eco-label paints & coatings.			X	X	X	X	45	44	43	8	30 - 250	1.01
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	Early hardness, sandability with superior chemical resistance; blend vehicle with polyurethanes	X	X	X				57	41.5	39	7.5	10 - 300	1.04
Carbaset® 7722	Acrylic Emulsion	Low VOC, adhesion, stain blocking, & scrub resistance in all sheens					X		45	50	48	8.4	40 - 800	1.06
Carbaset® 7733	Acrylic Emulsion	Low VOC, exterior durability & scrub resistance in high gloss formulations					X		21	50	46	8.4	40 - 800	1.06
Carbaset® AMO 400	Acrylic Oil Modified Copolymer	Renewable, low VOC, high melt temperature for high speed sanding, improved toughness, black heel mark & abrasion resistance; blend vehicle with other resins	X	X	X	X		X	12	40	37.5	7.5	<500	1.06
Carbaset® CR 726*	Self-crosslinking Acrylic Emulsion	Low VOC & excellent hardness	X	X	X	X			35	42	41	8	50 - 600	1.05
Carbaset® CR 7181	Self-crosslinking Acrylic Emulsion	Hard, excellent chemical resistance, air & forced dry compatible; adhesion to wood, metal, & plastic		X	X				90	42	39.1	9	50	1.06
Carbaset® 3142	Styrene Acrylic Emulsion	Low VOC, high gloss, exceptional block & chemical resistance, multi-substrate adhesion, exterior durability; alkyd-like application			X	X	X		7	41	40	7	10-500	1.02
Carbaset® CA 7147	Acrylic Emulsion	High gloss, fine particle size, fast drying, non-yellowing, water, weather, & dirt pick-up resistant					X	X	6	46	45	8.5	300 - 1200	1.01

*Produced in multiple facilities; product name may vary

POLYURETHANE DISPERSION TECHNOLOGIES FOR WOOD COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS				MFFT (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			FLOORS	CABINETS	FURNITURE	WINDOWS & DOORS						
Aptalon™ W8060	Self-crosslinking Polyurethane Dispersion - Polyamide	Renewable, superior chemical resistance, balance of hardness, abrasion & scratch resistance	X		X		59	36	33	7.5	<500	1.05
Aptalon™ W8062	Self-crosslinking Polyurethane Dispersion - Polyamide	Lower VOC, improved scuff & black heel mark resistance	X	X	X		31	36	33	7.5	<500	1.04
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	Low gloss without matting agents & excellent abrasion resistance	X	X	X		61	35	34.2	7.5	<500	1.04
Aptalon™ W8034	Self-Matting Polyurethane Dispersion - Polyamide	Low VOC, low gloss without matting agents & excellent abrasion resistance	X	X	X		5	35	33	8	<500	1.03
Aptalon™ 8080HS	High-solids Polyurethane Dispersion - Polyamide	Renewable, rapid hardness, excellent chemical, mar & scuff resistance, crosslinkable	X		X	X	45	50	50	7.5	<500	1.05
Sancure™ 970	Polyurethane Dispersion - Polyester	Adhesion to multiple substrates, excellent hardness & chemical resistance, crosslinkable	X		X	X	50	42	41	8	<500	1.06
Turboset™ 1000	Self-crosslinking Polyurethane Hybrid Dispersion	Rapid hardness, excellent chemical, mar & scuff resistance, crosslinkable	X	X	X		23	39	36	7.5	<500	1.05
Turboset™ 2027	Self-crosslinking Polyurethane Dispersion - Polyester	Excellent chemical & stain resistance	X		X		22.5	40	35	8	<500	1.07
Turboset™ Ultra Eco	Self-crosslinking Polyurethane Dispersion - Polyester	Low VOC, superior black heel mark resistance, excellent hardness & chemical resistance	X		X		45	36	35	7.5	<400	1.04
Sancure™ AU 4050	Self-crosslinking Acrylic/Polyester Polyurethane Hybrid Dispersion	Non-yellowing, excellent chemical, abrasion & scuff resistance	X		X	X	15	36	32	8	<125	1.05



ACRYLIC TECHNOLOGIES FOR BUILDING & CONSTRUCTION COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS				MFFT (°C)	TG (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			LIQUID ROOF	VERTICAL MASONRY	HORIZONTAL MASONRY	MORTAR MODIFIER							
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	Low VOC, Exceptional chemical & block resistance & early hardness		X	X		45		44	43	8	30 - 250	1.01
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	Robust water resistance, high hardness, outstanding gloss/wet look, excellent chemical & mar resistance			X		57		41.5	39	7.5	10 - 300	1.04
Carbaset® 7722	Acrylic Emulsion	Low VOC, good scrub resistance, early block & print resistance, pigmentable		X	X		45		50	48	8.4	40 - 800	1.06
Carbaset® 7733	Acrylic Emulsion	Low VOC, high gloss, inherent stain removal & washability, early block resistance & great flow & leveling		X	X		21		50	46	8.4	40 - 800	1.06
Carbaset® AE 960*	Acrylic Emulsion	Low VOC, excellent dirt pick-up, balance of elongation & tensile strength, outstanding water resistance, weathering & crack bridging also suitable for ASTM D6083 compliant paints & coatings.	X	X			45	-25	56	55	8.2	<2000	1.02
Carbaset® CA 7147	Acrylic Emulsion	Low VOC, small particle size, alkali resistance, high water vapor permeability & low CO2 permeability		X	X		6		47	46	8.8	300-1200	1.01
Carbaset® CA 7107	Acrylic Emulsion	Low VOC, excellent water, alkali & weathering resistance	X	X			0	8	50	47	8.5	9000	1.05
Carbaset® CA 7100RC	Styrene Acrylic Emulsion	Low VOC, balance of mechanical properties, excellent adhesion to most masonry substrates at high PVC loading, water & alkali resistance	X	X			0	-10	50	49	8.3	8.000-11000	1.01
Carbaset® CA 7160RC	Styrene Acrylic Emulsion	Low VOC, alkali resistant, excellent adhesion to most masonry substrates at high PVC loading		X	X		21	18	50	49	8.3	2500-5000	1.01
Carbaset® CA 7120RC	Styrene Acrylic Emulsion	Low VOC, excellent water, alkali & dirt pick-up resistance, balance of elasticity & tensile strength. Great adhesion to most masonry substrates including terracotta tiles.	X	X			0	0	48	47	8.3	8000-12500	1.01
Carbaset® CR 7185	Acrylic Emulsion	Excellent water retention, concrete curing properties & high alkali resistance			X		44		42	41	8.5	10-300	1.03
Carbaset® CA 600*	Acrylic Emulsion	Early water resistance, fast drying, great substrate penetration, alkaline, blushing, efflorescence, chemical resistance, non-yellowing & exterior exposure			X		35	55	42	41	8.3	41	1.06
Carbaset® CA 1009*	Acrylic-Polyurethane Polymer	Low VOC, minimal water uptake & capillary absorption, superior water & bitumen bleed through resistance, excellent exterior durability & heat stable.	X	X			2	5	55	53	8	150 - 800	1.1
Carbaset® RP 7350	PVDC Emulsion	Low VOC, excellent corrosion resistance & low permeability	X				13.5		60	50.4	1.0 - 2.2	85	1.28
Carbaset® RPT 2000A	Acrylic Copolymer Emulsion	Low VOC, superior adhesion to wide range of substrates & great bitumen bleed through resistance	X				45	10	55	53	8.5	100 - 15000	1.04
Carbaset® RPT 3030	Acrylic Emulsion	Low VOC, excellent low temperature elasticity, ASTM D6083 compliance capable, & adhesion to EPDM	X	X			0	-35	55	53	8	200-1200	1.06
Carbaset® SA 850*	Acrylic Copolymer Emulsion	Low VOC, robust crack-bridging performance & weatherability, resistant to chalking, fading, & water penetration, excellent dirt pick-up, efflorescence, alkali properties	X	X			45	10	55	53	8.5	100 - 15000	1.04
Carbaset® 3142	Styrene Acrylic Emulsion	Low VOC, high gloss coatings, exterior durability, good block & stain resistance, multi-substrate adhesion; alkyd-like application		X			7		41	40	7	10-500	1.02
Carbaset® X-Flex 100	High Solids Acrylic Emulsion	Low VOC, highly elastic cement compatible binder, excellent alkali & water resistance				X		-40	60	60	8.5	100-1000	1.01
Carbaset® XM200	Acrylic Emulsion	Low VOC, cement compatible binder, enhances adhesion & mechanical properties of cementitious formulations				X	0	19	48.5	48	8.5	25	1.01
Carbaset® PL 958*	Acrylic Emulsion	Low VOC, high tensile strength for clear & pigmented temporary protection & excellent chemical resistance. Peelable coatings.					0		46.8	43	8	40-125	1.07
Carbotac® 1811	Acrylic Emulsion	Low VOC, long open time polymer for bonding bridge masonry applications				X	0	-43	55	53	3.5	120	1.03

*Produced in multiple facilities; product name may vary

POLYURETHANE DISPERSION TECHNOLOGIES FOR BUILDING & CONSTRUCTION COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS			MFFT (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			LIQUID ROOF	VERTICAL MASONRY	HORIZONTAL MASONRY						
Aptalon™ 8o8oHS	High-solids Polyurethane Dispersion - Polyamide	Renewable, rapid hardness, excellent chemical, mar & scuff resistance			X	45	50	50	7.5	<500	1.05
Aptalon™ W8o34	Self-Matting Polyurethane Dispersion - Polyamide	Low VOC, low gloss without matting agents & excellent abrasion resistance			X	5	35	33	8	<500	1.03
Aptalon™ W8o6o	Self-crosslinking Polyurethane Dispersion - Polyamide	Renewable, superior chemical resistance, balance of hardness & abrasion resistance & scratch resistance			X	59	36	33	7.5	<500	1.05
Aptalon™ W8o62	Self-crosslinking Polyurethane Dispersion - Polyamide	Lower VOC, improved scuff & black heel mark resistance			X	31	36	33	7.5	<500	1.04
Aptalon™ M81oo	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance			X	58	37	34	7.5	<500	1.04
Sancure™ 2oo41	Polyurethane Dispersion - Polyester	Cosolvent-free, excellent hardness, compatible with acrylics; crosslinkable	X		X	22	34	30	8	150	1.05
Sancure™ 861	Polyurethane Dispersion - Polyether	Low VOC, cosolvent-free, hydrolytic & aging stability, alkali, abrasion & chemical resistance	X	X		<5	40	39	7.5	<90	1.02
Sancure™ 2oo25F	Aliphatic Polyurethane Dispersion - Polyester	Low VOC, provides enhanced durability when blended with acrylics	X	X		<5	48	45	8	<500	1.05
Sancure™ 97o	High Solids Polyurethane Dispersion - Polyester	Chemical & abrasion resistance; crosslinkable			X	50	42	41	8	<500	1.06
Sancure™ AU4o5o	Self-crosslinking Acrylic/ Polyester Polyurethane Hybrid Dispersion	Non-yellowing, excellent chemical, abrasion & scuff resistance			X	15	36	32	8	<125	1.05
Turboset™ Ultra Eco	Self-crosslinking Polyurethane Dispersion - Polyether	Low VOC, superior black heel mark resistance, excellent hardness & chemical resistance			X	<5	36	35	7.5	<400	1.04
Turboset™ 2o27	Self-crosslinking Polyurethane Dispersion - Polyester	Cosolvent-free, excellent chemical resistance & durability			X	22.5	40	35	8.7	<500	1.07

SOLUTION ACRYLIC TECHNOLOGIES FOR BUILDING & CONSTRUCTION COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS			SOLVENT	ACID NUMBER	TG (°C)	% WEIGHT SOLIDS	VISCOSITY (CPS)	SPECIFIC GRAVITY
			LIQUID ROOF	VERTICAL MASONRY	HORIZONTAL MASONRY						
Doresco® L91-1X	Solvent-borne Acrylic Polymer in Xylene	Hard solvent-borne acrylic designed for general purpose concrete coating		X		Xylene	<10	57	49	5000 - 8000	0.985
Doresco® M6A	Solvent-borne Thermoplastic Acrylic in Xylene	Exterior durability & adhesion to multiple substrates	X	X	X	Xylene	<10	61	50	5-7	0.98
Doresco® T6T	Solvent-borne Thermoplastic Acrylic in Toluene	Quick drying road-markings for high traffic areas			X	Toluene	<10	61	50	3700	0.97
Doresco® T5T6o	Solvent-borne Thermoplastic Acrylic in Toluene	Quick drying road-marking for medium traffic areas; internally plasticized version of Doresco T6T			X	Toluene	<10	43	60	7000	1.00



ACRYLIC & PVDC TECHNOLOGIES FOR INDUSTRIAL COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS				MFFT (°C)	TG (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			DTM	PRIMER	TOPCOAT	TEMPORARY COATING							
Carbaset® 514*	Alkali Strippable Acrylic Dispersion	High gloss, fast drying, excellent hardness & adhesion				X	10	28	40	38	6.6	100 - 500	1.05
Carbaset® 560	Alkali Strippable Acrylic Dispersion	Water & UV resistance, excellent mechanical stability & adhesion				X	17	47	27	24.5	7.6	<200	1.03
Carbaset® 441	Peelable Acrylic Emulsion	Balance of adhesion & cohesion for strippability, excellent toughness & durability				X	18	23	45	42	8	100	1.04
Carbaset® CR 3090	Stryrene Acrylic Emulsion	Great corrosion & weathering resistance; adhesion to CRS, Phasphated & galvanized steel	X	X	X		33	37	45	42	8.5	<500	1.05
Carbaset® CR 3100	Stryrene Acrylic Emulsion	Low VOC, great corrosion & weathering resistance; adhesion to CRS, HRS & galvanized steel	X	X	X		9	28	43.5	41	8	<500	1.05
Carbaset® CR 7185	Acrylic Emulsion	Fast dry, resistant to gas, solvents, impact, water & humidity; adhesion to Phasphated & stainless steel	X	X	X		40		42	40	8.3	5-120	1.03
Carbaset® CR 765*	Stryrene Acrylic Emulsion	Balance of performance properties, high gloss, water & humidity resistance, reactive pigment stability; adhesion to CRS, Phasphated, aluminum, copper, stainless steel	X	X	X		34		41	40.7	8	10 - 150	1.03
Carbaset® PL 3127	Peelable Acrylic Copolymer Emulsion	Low VOC, fast drying, & corrosion resistance				X	5	15	44	42.8	7.8	150	1.05
Carbaset® PL 958*	Peelable Acrylic Copolymer Emulsion	Low VOC, high elasticity, solvent & breaking resistance				X	<3		46	43.4	7	40 - 125	1.07
Carbaset® CR 7162E	Styrene Acrylic Emulsion	Air & force dry, gloss & semi-gloss, corrosion & humidity resistance; adhesion to plastic, metal & masonry	X	X	X		23		41.5	39	8	10-100	1.03
Carbaset® 3142	Styrene Acrylic Emulsion	Gloss & semi-gloss, wet adhesion, block & sag resistance, interior & exterior architectural; alkyd like application	X	X	X		7		41.5	40	8.5	10-500	1.02
Permax™ 805*	PVDC Emulsion	Low VOC, humidity resistant, increased shelf-life & in-can stability; adhesion to aluminum, CRS, Bonderite 1000, ground & galvanized steel	X	X			13.5		60	50.4	1.0 - 2.2	85	1.28
Permax™ 805B	PVDC Emulsion	Low VOC, small particle size, low MVTR, excellent corrosion resistance & durability, adhesion to aluminum, CRS, ground & galvanized steel	X	X			13.5		60	50	1.8	85	1.28

*Produced in multiple facilities; product name may vary

POLYURETHANE TECHNOLOGIES FOR INDUSTRIAL COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS			MFFT (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			DTM	PRIMER	TOPCOAT						
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance			X	58	37	34	8	<500	1.04
Aptalon™ M8120	Self-crosslinking Polyurethane Dispersion - Polyamide	Excellent adhesion to metal surfaces, extraordinary hardness and durability in a 1k WB DTM, outstanding chemical & corrosion resistance.	X	X	X	50	37	34	8.5	<500	1.09
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	Low gloss without matting agents & excellent abrasion resistance			X	61	35	34.2	7.5	<500	1.04
Aptalon™ W8034	Self-Matting Polyurethane Dispersion - Polyamide	Low VOC, low gloss without matting agents & excellent abrasion resistance			X	5	35	33	8	<500	1.03
Sancure™ 825	Aliphatic Polyurethane Dispersion - Polyester	High gloss, UV stable, resistant to water, alcohol, alkali, & abrasion; adhesion to ferrous & non-ferrous metals	X	X	X	<5	34	31	8.5	<425	1.04
Sancure™ 970	Polyurethane Composite - Polyester	Great chemical, abrasion, & alkali resistance, crosslinkable; adhesion to ferrous & non-ferrous metals	X	X	X	50	42	41	8	<500	1.06

*Produced in multiple facilities; product name may vary



SOLUTION ACRYLIC TECHNOLOGIES FOR INDUSTRIAL COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS			SOLVENT	ACID NUMBER	TG (°C)	% WEIGHT SOLIDS	VISCOSITY (CPS)	SPECIFIC GRAVITY
			DTM	PRIMER	TOPCOAT						
Doresco® AC4-74	Solvent-borne Thermoplastic Acrylic	Adhesion promoted resin, tough & flexible, exterior durability, block resistance & bake system capable; adhesion to aluminum, primed & unprimed steel	X			Toluene	N/A	50	45	8000	0.96
Doresco® OH60	Hydroxylated Acrylic (3% OH Solids)	High gloss, balance of hardness, flexibility & impact resistance; adhesion to galvanized steel; crosslinkable with isocyanates	X	X	X	MPA/Xylene (1:1)	<10	14	50	1000-2500	0.96
Doresco® OH65	Hydroxylated Acrylic (2% OH Solids)	High gloss, balance of hardness, flexibility & impact resistance; adhesion to metal surfaces; crosslinkable with isocyanates	X	X	X	Xylene	<11	27	50	1000-3000	0.96
Doresco® OH38	Hydroxylated Acrylics (4% OH Solids)	Excellent gloss & hardness, quick drying, chemical, UV & weather resistance; adhesion to wood, plastics, & metal	X	X	X	MPA/Xylene (1:1)	<12	50	42	300-700	0.98
Doresco® M6A	High Solids Solvent-borne Thermoplastic Acrylic	Non-yellowing, quick dry, excellent chemical resistance & weathering; adhesion to metal surfaces	X	X	X	Xylene	<10	61	50	800-2500	1.00
Doresco® Cl7208	Solvent-borne Thermoplastic Acrylic	Adhesion to galvanized steel, multipurpose primers, gloss enamels	X	X	X	Xylene	<10	39	49	250-1000	0.97

TRANSPORTATION COATING TECHNOLOGIES

RESIN TECHNOLOGIES FOR TRANSPORTATION COATINGS

PRODUCT	POLYMER TYPE	KEY BENEFITS	APPLICATIONS		MFFT (°C)	% WEIGHT SOLIDS	% VOLUME SOLIDS	pH	VISCOSITY (CPS)	SPECIFIC GRAVITY
			PRIMER	TOPCOAT						
ACRYLIC TECHNOLOGIES										
Carboset® CR 7181	Self-Crosslinking Acrylic Emulsion	High gloss, excellent UV resistance; adhesion to a variety of plastics including ABS, Lexan, Melamine, & Noryl	X	X	90	42	39	9	6 - 50	1.06
Carboset® PC 27	Self-Crosslinking Acrylic Emulsion	Superior chemical resistance to sunscreens, insect repellents, surface cleaners & protectants, excellent scratch, abrasion & print resistance; adhesion to a variety of plastics including ABS, Lexan, Noryl	X	X	90	42	40	8.5	50 - 200	1.05
POLYURETHANE TECHNOLOGIES										
Sancure™ 20025F	Aliphatic Polyurethane Dispersion - Polyester	Low VOC, durable, elastic, crosslinkable; adhesion to nylon & polyester, heat sealable		X	< 5	48	45	8	<500	1.05
Sancure™ PC 55	Aliphatic Polyurethane Dispersion - Polyester/Polycarbonate	Low VOC, balance of mar resistance with soft tactile feel, superior chemical resistance to sunscreens, insect repellents, surface cleaners & protectants, & excellent UV resistance		X	< 5	42	39	7	<500	1.05
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	Balance of hardness & abrasion resistance, superior chemical & hydrolytic resistance		X	58	37	34	7.5	<500	1.04



ACRYLIC/PVDC TECHNOLOGIES

PRODUCT	POLYMER TYPE	% WEIGHT SOLIDS	MFFT (°C)	APEO-FREE ¹	FORMALDEHYDE-FREE ¹	AVAILABILITY ²
ACRYLIC TECHNOLOGIES						
Carbaset® 2951	Self-crosslinking Acrylic Copolymer Emulsion	44	<5	Yes	Yes	NA EMEAI
Carbaset® 2968	Self-crosslinking Acrylic Emulsion	41.5	57	Yes	Yes	NA EMEAI
Carbaset® 3142	Styrene Acrylic Emulsion	41	7	Yes	Yes	EMEAI
Carbaset® 441	Peelable Acrylic Emulsion	45	18	Yes	No	NA
Carbaset® 514 ³	Alkali Strippable Acrylic Emulsion	40	10	Yes	Yes	NA EMEAI
Carbaset® 560	Alkali Strippable Acrylic Emulsion	27	17	Yes	Yes	NA EMEAI
Carbaset® 7722	Acrylic Emulsion	50	<5	Yes	No	NA EMEAI
Carbaset® 7733	Acrylic Emulsion	50	21	Yes	No	NA EMEAI
Carbaset® AE 960 ³	Acrylic Emulsion	56	<5	Yes	Yes	NA EMEAI
Carbaset® AMO 400	Acrylic Oil Modified Copolymer	40	12	Yes	Yes	NA EMEAI
Carbaset® CA 1009 ³	Acrylic-Polyurethane Polymer	55	2	Yes	Yes	NA EMEAI
Carbaset® CA 600 ³	Acrylic Emulsion	42	35	Yes	Yes	NA EMEAI
Carbaset® CA 7100RC	Styrene Acrylic Emulsion	48	0	Yes	Yes	EMEAI
Carbaset® CA 7107	Acrylic Emulsion	50	0	Yes	No	EMEAI
Carbaset® CA 7120RC	Styrene Acrylic Emulsion	48	0	Yes	Yes	NA
Carbaset® CA 7147	Acrylic Emulsion	47	6	Yes	Yes	EMEAI
Carbaset® CA 7160RC	Styrene Acrylic Emulsion	50	21	Yes	Yes	EMEAI
Carbaset® CR 3090	Styrene Acrylic Emulsion	45	33	Yes	Yes	NA
Carbaset® CR 3100	Styrene Acrylic Emulsion	43.5	9	Yes	Yes	NA
Carbaset® CR 7162E	Styrene Acrylic Emulsion	41.5	23	Yes	Yes	EMEAI
Carbaset® CR 7181	Self-crosslinking Acrylic Emulsion	42	90	Yes	Yes	NA EMEAI
Carbaset® CR 7185	Acrylic Emulsion	42	40	Yes	Yes	NA EMEAI
Carbaset® CR 726 ³	Self-crosslinking Acrylic Emulsion	42	35	Yes	Yes	NA EMEAI
Carbaset® CR 765 ³	Styrene Acrylic Emulsion	41	34	Yes	Yes	NA EMEAI
Carbaset® CR 795	Acrylic Emulsion	45	24	Yes	Yes	NA EMEAI
Carbaset® PC 27	Self-crosslinking Acrylic Polymer	42	90	Yes	Yes	NA EMEAI
Carbaset® PL 3127	Peelable Acrylic Copolymer Emulsion	44	5	Yes	Yes	NA EMEAI
Carbaset® PL 958 ³	Peelable Acrylic Copolymer Emulsion	46	<3	Yes	No	NA EMEAI
Carbaset® RPT 2000 ³	Acrylic Copolymer Emulsion	55	<5	No	Yes	NA EMEAI
Carbaset® RPT 3030	Acrylic Emulsion	55	0	Yes	No	NA EMEAI
Carbaset® SA 850 ³	Acrylic Copolymer Emulsion	55	<5	No	Yes	NA EMEAI
Carbaset® X-Flex 100	High Solids Acrylic Emulsion	60	0	-	No	EMEAI
Carbaset® XM200	Acrylic Emulsion	48.5	Tg = 19	Yes	No	NA EMEAI
Carbotac® 1811	Acrylic Emulsion	55	0	Yes	No	NA EMEAI
PVDC TECHNOLOGY						
Permax™ 805	PVDC Emulsion	60	13.5	Yes	Yes	NA
Permax™ 805B	PVDC Emulsion	60	13.5	Yes	Yes	EMEAI
Carbaset® RP 7350	PVDC Emulsion	60	13.5	Yes	Yes	NA EMEAI

¹Ingredient not intentionally added to the composition or used in manufacture of Lubrizol product.

²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

³Produced in multiple facilities; product name may vary.

POLYURETHANE DISPERSION TECHNOLOGIES

PRODUCT	POLYMER TYPE	% WEIGHT SOLIDS	MFFT (°C)	APEO-FREE ¹	NMP-FREE ¹	AVAILABILITY ²
Aptalon™ 8080HS	High-solids Polyurethane Dispersion - Polyamide	50	45	Yes	Yes	NA EMEAI
Aptalon™ M8100	Self-crosslinking Polyurethane Dispersion - Polyamide	37	58	Yes	Yes	NA EMEAI
Aptalon™ M8120	Self-crosslinking Polyurethane Dispersion - Polyamide	37	50	Yes	Yes	NA EMEAI
Aptalon™ W8030	Self-Matting Polyurethane Dispersion - Polyamide	35	61	Yes	Yes	NA EMEAI
Aptalon™ W8034	Self-Matting Polyurethane Dispersion - Polyamide	35	5	Yes	Yes	NA EMEAI
Aptalon™ W8060	Self-Crosslinking Polyurethane Dispersion - Polyamide	36	59	Yes	Yes	NA EMEAI
Aptalon™ W8062	Self-Crosslinking Polyurethane Dispersion - Polyamide	36	31	Yes	Yes	NA EMEAI
Sancure™ 20025F	Aliphatic Polyurethane Dispersion - Polyester	48	<5	Yes	Yes	NA EMEAI
Sancure™ 20041	Polyurethane Dispersion - Polyester	34	22	Yes	Yes	NA
Sancure™ 825	Aliphatic Polyurethane Dispersion - Polyester	34	<5	Yes	-	NA EMEAI
Sancure™ 861	Polyurethane Dispersion - Polyether	40	<5	Yes	Yes	NA EMEAI
Sancure™ 970	Polyurethane Dispersion - Polyester	50	42	Yes	Yes	NA EMEAI
Sancure™ AU4050	Self-crosslinking Acrylic/Polyester Polyurethane Hybrid Dispersion	36	15	Yes	Yes	NA EMEAI
Sancure™ PC 55	Aliphatic Polyurethane Dispersion - Polyester/Polycarbonate	42	<5	Yes	Yes	NA
Turboset™ 1000	Self-crosslinking Polyurethane Hybrid Dispersion	39	23	Yes	Yes	NA EMEAI
Turboset™ 2027	Self-Crosslinking Polyurethane Dispersion - Polyester	40	22.5	Yes	Yes	NA EMEAI
Turboset™ Ultra Eco	Self-Crosslinking Polyurethane Dispersion - Polyester	36	<5	Yes	Yes	NA

¹Ingredient not intentionally added to the composition of Lubrizol product.

²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

SOLUTION ACRYLIC TECHNOLOGIES

PRODUCT	POLYMER TYPE	SOLVENT	% WEIGHT SOLIDS	TG (°C)	AVAILABILITY ²
Doresco® AC4-74	Solvent-borne Thermoplastic Acrylic	Toluene	45	50	NA
Doresco® C17208	Solvent-borne Thermoplastic Acrylic	Xylene	49	39	EMEAI
Doresco® L91-1X	Solvent-borne Acrylic Polymer	Xylene	49	57	NA
Doresco® M6A	Solvent-borne Thermoplastic Acrylic	Xylene	50	61	EMEAI
Doresco® OH38	Hydroxylated Acrylics (4% OH Solids)	MPA/Xylene (1:1)	42	50	EMEAI
Doresco® OH60	Hydroxylated Acrylic (3% OH Solids)	MPA/Xylene (1:1)	50	14	NA EMEAI
Doresco® OH65	Hydroxylated Acrylic (2% OH Solids)	Xylene	50	27	NA EMEAI
Doresco® T5T60	Solvent-borne Thermoplastic Acrylic	Toluene	60	43	NA EMEAI
Doresco® T6T	Solvent-borne Thermoplastic Acrylic	Toluene	50	43	EMEAI

¹Ingredient not intentionally added to the composition of Lubrizol product.

²Product availability is subject to change without notice. Please contact your local representative for current product information and availability in other regions.

NORTH AMERICA

Lubrizol Advanced Materials, Inc.
9911 Brecksville Road
Brecksville, OH 44141 USA
+1.888.234.2436

EUROPE

Lubrizol Limited
PO Box 42, Hexagon Tower
Blackley, Manchester
M9 8ZS United Kingdom
+44 161 721 6800

ASIA-PACIFIC

Lubrizol Specialty Chemicals
(Shanghai) Co., Ltd
10/F, Park Center International
No. 1088 Fang Dian Road
Shanghai 201204, PR China
+8621-3866-0366

SOUTH AMERICA

Lubrizol do Brasil Aditivos Ltda
Avenida Nove de Julho, 3653
Jardim Paulista
Sao Paulo – SP
01407-000
+55.11.4097.0250

Visit us at:

www.lubrizol.com/coatings

Lubrizol Performance Coatings is a market-driven innovator of specialty chemicals for advanced coatings, inks and composites that enable the world to move cleaner, create smarter and live better. Our portfolio of resin and additive technologies solve challenges across a wide range of markets and applications. Formulators choose Lubrizol to achieve unique durability, functionality, sustainability and aesthetic capabilities. More than just a supplier, we are a collaborator with extensive experience in surface protection, dispersion, adhesion, and barrier properties – working closely with customers to explore and develop truly differentiated solutions.

The Lubrizol logo features the word "Lubrizol" in a bold, italicized, sans-serif font. A blue swoosh underline is positioned beneath the letters "i", "z", "i", and "o".

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Product safety information required for safe use is not included. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LUBRIZOL REPRESENTATIVE, OR DISTRIBUTOR.