

Lubrizol® 2062H Adhesion Promoter

LUBRIZOL 2062H is an isobutanol solution of an acid and hydroxyl functional polymer that improves the adhesion of a wide range of industrial coatings to ferrous metal and aluminum substrates. It is also an effective metal pre-treatment and can be used to stabilize metallic effect pigments in waterborne applications.

Adhesion Promoter for metal substrates

FEATURES AND BENEFITS

- Adhesion Promotion
- Corrosion Inhibitor
- Flash Rush Inhibitor
- Passivation

CHARACTERISTICS

Characteristic Name	Value
Acid Number (mg KOH/g)	63
Active Content (% wt.)	61
Appearance	Amber viscous liquid
Density (g/ml)	1.0
Flash Point (°C)	32 (90)
Solvent	Isobutanol
Viscosity (cP)	<25000

REGULATORY

- Nestle Guidance | Note: Packaging Inks
- Swiss Ordinance (Annex 10 to the Ordinance)

APPLICATIONS

- Industrial OEM Coatings
- Protective Coatings
- Transportation Coatings

AVAILABLE REGIONS

- Asia Pacific
- EMEA
- Latin America
- North America

RECOMMENDED STORAGE AND RE-TEST DATE

Lubrizol recommends retesting quality after 730 days. See SDS for storage conditions and handling instructions.

REGULATORY STATUS

Please see the product's current material safety data sheet, SDS, for regulatory information. You can request an SDS at www.lubrizol.com/coatings.

Should you have questions on additional topics, please feel free to contact your Lubrizol representative or one of our regional Customer Assistance groups listed here:

America: AmerLZAMCustomerAssistance@Lubrizol.com | Europe: EMEAICustomerAssistance@Lubrizol.com |

Asia: APCustomerAssistance@Lubrizol.com | Brazil: BrazilQualityLZAM@Lubrizol.com

DISCLOSURE

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. Product safety information required for safe use is not included. **BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LUBRIZOL REPRESENTATIVE, OR DISTRIBUTOR.**

Trademarks owned by The Lubrizol Corporation or its affiliates. © The Lubrizol Corporation 2020, All Rights Reserved.