

Sancure™ 2026C Polyurethane Dispersion

Aliphatic Waterborne Urethane Polymer

Sancure™ 2026C dispersion forms a soft, flexible, clear film upon drying. Its excellent elongation, along with its toughness, makes it a good candidate for textile applications. Sancure 2026C can be blended with a variety of acrylic polymers.

FEATURES AND BENEFITS

- Adhesion
- Crosslinkable
- Flexible
- Softness
- Toughness

CHARACTERISTICS

Characteristic Name	Value
% Weight Solids	38.0-42.0
Appearance	Opaque
Brookfield Viscosity (cps)	500 max
Charge	Anionic
Density (lb/gal @ 25 °C)	8.86
Elongation (%)	450-800
Freeze/Thaw Stability	5 Cycles
Tensile (psi or Mpa)	940-7700 psi
VOC (g/L)	187
pH Value	7.0-9.0

APPLICATIONS

- Apparel Coatings

AVAILABLE REGIONS

- Asia Pacific
- EMEA
- Latin America
- North America

REGULATORY STATUS

Please see the product's current material safety data sheet, SDS, for regulatory information. You can request an SDS at www.lubrizol.com/coatings.

Should you have questions on additional topics, please feel free to contact your Lubrizol representative or one of our regional Customer Assistance groups listed here:

America: AmerLZAMCustomerAssistance@Lubrizol.com | Europe: EMEAICustomerAssistance@Lubrizol.com |

Asia: APCustomerAssistance@Lubrizol.com | Brazil: BrazilQualityLZAM@Lubrizol.com

DISCLOSURE

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. Product safety information required for safe use is not included. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LUBRIZOL REPRESENTATIVE, OR DISTRIBUTOR.

Trademarks owned by The Lubrizol Corporation or its affiliates. © The Lubrizol Corporation 2020, All Rights Reserved.