



Lubrizol

WOOD COATINGS

TURBOSET™ ULTRA PRO

SELF-CROSSLINKING WATERBORNE POLYURETHANE DISPERSION

For superior-looking wood floor finishes that are durable and easy to apply, turn to Lubrizol Performance Coatings. New Turboset™ Ultra Pro urethane dispersion eliminates the need for a separate crosslinker, yet delivers performance comparable to two-component waterborne systems.

Fast, tough and smart

Designed to exhibit exceptional floor-wear characteristics, such as black heel mark and scuff resistance, Turboset™ Ultra Pro is ideal for sports and recreational floors. Its ease of use and extended pot life also make it an excellent candidate for high-end residential and commercial floor finishes.

How it works

The nano-sized polymer particles in Turboset™ Ultra Pro urethane dispersion crosslink after application and continue while drying. Turboset™ Ultra Pro exhibits outstanding long-term dispersion stability in pH ranges from neutral and above. As water and cosolvent leave the film and the pH of the film drops, curing takes place. By reducing application time, the formula allows for multiple coats per day.

Additional benefits

In addition, Turboset™ Ultra Pro urethane dispersion makes coating application easier and safer than ever. The single stage system has an extended pot life that prolongs the ability to use the material and minimizes unwanted waste. It also eliminates many potential health and environmental hazards, including reduced odor and waste disposal.

**FASTER, TOUGHER
AND MORE VERSATILE,
TURBOSET™ ULTRA
PRO IS CHANGING
THE GAME FOR FLOOR
FINISHES**

- ONE LESS STEP (NO CROSSLINKING) MEANS A HUGE LEAP FORWARD IN PRODUCTIVITY
- NEXT GENERATION LEGENDARY TECHNOLOGY FOR SPORTS FLOORS AND OTHER HIGH-END RESIDENTIAL AND COMMERCIAL FLOOR FINISHES
- SUPERB APPEARANCE AND DURABILITY
- EASY TO USE WITH REDUCED ODOR AND HEALTH RISKS

www.lubrizolcoatings.com

FEATURES & BENEFITS

- ONE-COMPONENT; NO ADDITIONAL CROSSLINKER REQUIRED
- IDEAL FOR SPORTS FLOORS AND HIGH-END RESIDENTIAL AND COMMERCIAL FLOORS
- EXCELLENT BLACK HEEL MARK RESISTANCE
- DRIED FILM APPEARANCE COMPARABLE TO HIGH VOC FINISHES
- POLYMER ACHIEVES 90 GLOSS UNITS AT 60° FOR SPORTS FLOORS
- LOWER HEALTH RISKS AND LESS WASTE
- MFMA COF COMPLIANT—MEETS SLIP REQUIREMENTS FOR WOOD FLOORS
- POLYMER AND FORMULATIONS HAVE EXCELLENT LONG-TERM STABILITY

Visit us at:
www.lubrizolcoatings.com

TYPICAL PROPERTIES

APPEARANCE (WET)	LIGHT MILKY DISPERSION
TOTAL SOLIDS BY WEIGHT, %	36 ± 1
TOTAL SOLIDS BY VOLUME, %	33 ± 1
DENSITY, POUNDS/GALLON (GM/CM ³)	8.83 (1.06)
BROOKFIELD VISCOSITY, 25°C CPS, #2 SPINDLE, 100 RPM	<100
PH	7.5–8.0
TENSILE STRENGTH, PSI	4200
100% MODULUS, PSI	4000
% ELONGATION	110
VOLATILE ORGANIC CONTENT, WT%	6.8
FREEZE-THAW STABILITY	STABLE

Property values represent typical results only and are not to be considered specifications.

Lubrizol Advanced Materials, Inc.

9911 Brecksville Road, Cleveland, OH 44141
800.380.5397



The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.