

Hystretch™ V-95

Elastomeric Emulsion

PERFORMANCE COATINGS

PRODUCT DESCRIPTION

Hystretch™ V-95 is a fully saturated elastomeric terpolymer.

FEATURES/BENEFITS

- Outstanding weatherability
- Resilient
- Non-blocking
- Sprayable, foamable, and heat sensitizable
- Excellent mechanical stability as received
- APE-free and REACH compliant

PHYSICAL CHARACTERISTICS*

Appearance	White Liquid
Solids, Weight (%)	47.5 – 50%
pH	7.7 – 8.7
Viscosity, Brookfield (cps)	40 – 150 centipoise (LV spindle 1, 60 rpm)
Glass Transition, Tg °C	-29
Nature of Emulsion	Anionic

*Property values represent typical results only and are not to be considered specifications.

TYPICAL APPLICATIONS

Hystretch™ V-95 is suited to a variety of applications where durability, resiliency, and elastomeric behavior are a benefit. It is designed for application as supplied, or diluted with water, via typical spray, saturation or coating methods.

- Resilient non-woven binder
- Durable heavyweight paper saturant
- Industrial fabric finishes

SHELF LIFE/STORAGE

Hystretch™ V-95 should be stored in sealed containers between temperatures of 7 °C and 35 °C. In unopened containers the product is typically stable for 1 year. If the product is stored for longer periods then it should be fully validated by the customer prior to use. Lubrizol warrants that the product will meet specifications upon delivery to the customer but does not control product handling or storage after delivery. Please stir the product gently before use.

Recommended Retest Date, 365 days after date of manufacture.

REGULATORY STATUS

Please see the product's current safety data sheet, SDS, for regulatory information. It can be requested at www.lubrizol.com/coatings.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Product safety information required for safe use is not included. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LUBRIZOL REPRESENTATIVE, OR DISTRIBUTOR.