

# LUBRIZOL<sup>®</sup> 2064

Corrosion Inhibitor

## PRODUCT DESCRIPTION

LUBRIZOL 2064 is an overbased calcium sulfonate corrosion inhibitor dissolved in mineral oil. It is very effective for prevention of corrosion in alkyd or waterborne coatings and rust-proofing applications.

## FEATURES/BENEFITS

- Effective in waterborne coatings
- Provides corrosion inhibition for direct to metal coatings
- Effective in combination with corrosion inhibitive pigments
- Does not adversely affect coating storage stability

## PHYSICAL CHARACTERISTICS\*

Appearance	Tan, viscous, thixotropic gel
Active content (by weight)	60%
Density @ 15.6°C (60°F)	1.14
Flash point °C (°F)	185 (365)
Viscosity (cP) **	60,000

\* Property values represent typical results only and are not to be considered specifications.

\*\* Measured on a Brookfield RVF Viscometer, #7 spindle, 2 rpm @ 25°C (77°F)

## TYPICAL APPLICATIONS

LUBRIZOL 2064 is used in a variety of oil based and waterborne coatings, especially those based on styrenated acrylic latexes. The recommended addition rate of LUBRIZOL 2064 is 5-10%, based on total formula.

As a coating base in rustproofing applications, LUBRIZOL 2064 can be used at up to 40% on total formula.

LUBRIZOL 2064 should be incorporated during the grind stage of manufacturing.

## RECOMMENDED RETEST DATE (RRD) / STORAGE

Lubrizol 2064 is available in 200 liter (55-gallon) drums and 20 liter (5-gallon) pails.

RRD: 2 years.

For storage information, please refer to the current Safety Data Sheet.

## REGULATORY STATUS

Please refer to the current Safety Data Sheet (SDS) for regulatory information.

This can be requested at [www.lubrizolcoatings.com](http://www.lubrizolcoatings.com).

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Trademarks owned by The Lubrizol Corporation © The Lubrizol Corporation 2016, All Rights Reserved. Brecksville, August 2016

The Lubrizol logo consists of the word "Lubrizol" in a bold, sans-serif font. A blue swoosh underline is positioned beneath the letters "i", "z", "i", and "o".

[www.lubrizolcoatings.com](http://www.lubrizolcoatings.com)