

Technical Data Sheet

Type: Estane® 58206 is an 85A aromatic Polyester-Based Thermoplastic Polyurethane (TPU).

Features: Good Flexibility at Low Temperatures and Improved Weathering Performance.

Uses: Flat Die/Cast Film Extrusion and Hose/Profile Extrusion, Injection Molding.

Physical Properties	Value (Metric)	Unit	Test Method
Hardness (5 sec)	85 +/- 3	Shore A	ASTM D-2240
Specific Gravity	1.20		ASTM D-792
Tensile Strength	7000 (48.3)	psi (MPa)	ASTM D-412
Ultimate Elongation	550	%	"
Tensile Stress at:			
- 100 % Elongation	800 (5.5)	psi (MPa)	ASTM D-412
- 300 % Elongation	1500 (10.4)	psi (MPa)	"
Tear Strength			
Graves	500 (9.0)	lb/in (kg/mm)	ASTM D-624 (die C)
Trouser	130 (2.3)	lb/in (kg/mm)	ASTM D-470
Taber Loss (1000 rev)	0.0007 (20)	oz (mg)	ASTM D-3389 (H18, 1000g)
T _m (by DSC)	320 (160)	°F (°C)	Lubrizol Advanced Materials
T _g (by DSC)	-26 (-32)	°F (°C)	Lubrizol Advanced Materials

- Prior to testing samples were conditioned at 23°C for 48 hours.
- Based on extruded sheet (30 mils).
- Listed values are "typical (average) values" and should / cannot be applied for specification purposes.

Supply Form and Standard Packaging

- **Estane® 58206 TPU** is supplied in pellet form and packaged in 50 lb bags or 1000 lb boxes.

Material Preparation

- Prior to processing, **Estane® 58206 TPU** must be dried at **220°F (104°C)** for 2-4 hours.
- It is recommended to dry the material in a desiccant type dryer. Target dew point should be **-40°C**.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

Material Preparation

- **Estane® 58206 TPU** can be processed on any conventional extruder or injection molding machine.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



Recommended Starting Extrusion Temperature Profile:

	°F/°C
Zone 1	350/177
Zone 2	360/183
Zone 3	370/188
Zone 4	380/194
Adapter (5)	380/194
Die Zone 1	380/194
Die Zone 2	380/194

Melt Temp. Mid-Range: 375°F/191°C
Screen Pack Recommendation: 20/40/80

Recommended Starting Injection Molding Temperature Profile:

	°F/°C
Rear	350/177
Middle	370/188
Front	380/193
Nozzle	390/199
Melt Temperature*	390/199

*Melt temperature by pyrometer check of air shot

Fill Rate: Slow to Moderate
Screw RPM: 20-50
Back Pressure: 50 psi
Injection Pressure: 3,000-7,000 psi (21-48 MPa)
Molding Pressure: 2,000-4,000 psi (14-28 MPa)
Mold Shrinkage*: 0.014 in/in (cm/cm)

*Mold shrinkage was determined using ASTM D955 - 4" diameter x .125" thick molded disk. Actual shrinkage will vary with part size, design, and processing conditions. Please contact a Lubrizol Advanced Materials technical representative for more information.

Application Information: High Performance Film Polyester

Properties	Value (Metric)	Unit	Test Method
Tensile Set (200% elongation)	10	%	ASTM D-412
Kofler Melt Point	311 (155)	°F (°C)	Lubrizol Advanced Materials
Volume swell in Jet Fuel JP8	7.7	%	ASTM D-471
FDA 177.1680 (dry bulk foods)	No		
FDA 177.2600 (wet/fatty foods)	No		

For further information refer to Lubrizol Advanced Materials processing guides.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

