

Technical Data Sheet

Type: ESTANE® S185A is a Shore 87A, polyester based thermoplastic polyurethane (TPU).

Uses: Injection Molding, Extrusion

Physical Properties	Standard No.	Units	Value
Hardness	ASTM D2240	Shore A	87
Specific Gravity	ASTM D792	g/cm ³	1.20
Mechanical			
Tensile Stress:	ASTM D412	kgf/cm ²	
At 100% elongation			65
At 300% elongation			120
Tensile Strength	ASTM D412	kgf/cm ²	400
Ultimate Elongation	ASTM D412	%	650
Tear Resistance (Die C)	ASTM D624	kgf/cm	110
Abrasion Loss	ISO 4649	mm ³	30
Compression Set	ASTM D395		
At 23°C X22hr		%	15
At 70°C X22hr		%	35
Mold Shrinkage	ASTM D955	m/m	0.010
Thermal			
Vicat Softening Temperature	ASTM D1525	°C	95

*Test samples were annealed at 100°C and 24 hours at room temperature before testing.

**These are typical values and should not be used for specifications.

Injection Molding Guide

These settings are to be used only as a guide. This is a typical injection molding temperature profile based on the Test Machine (conditions based on a 75 ton machine with a general purpose screw – L/D 17 – Ø 35mm). The optimal run conditions for specific equipment will vary depending on the machine and mold design.

The Lubrizol Corporation (“Lubrizol”) hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.

