

Provisional Technical Data Sheet

Technical Data Sheet

Type: ESTANE® ZHF 58202 NAT 02 is a non halogen, flame retardant, aromatic polyether-based thermoplastic polyurethane (TPU).

Application: Extrusion

Physical Properties	Value (Metric)	Unit	Test Method
Hardness (1 sec)	91	ShA	ISO 868 (ASTM D-2240)
Specific Gravity	1.23	g/cm3	ISO 2781 (ASTM D-792)
Tensile Strength	28	MPa	ISO 527 (ASTM D-412)
Elongation @ break	632	%	ISO 527 (ASTM D-412)
Modulus @ 50%	7	MPa	ISO 527 (ASTM D-412)
Modulus @ 100%	8	MPa	ISO 527 (ASTM D-412)
Modulus @ 300%	10	MPa	ISO 527 (ASTM D-412)

- These are typical values & should not be used for establishing specifications.
- Based on extruded strips.

Application Specific Properties	Value (Metric)	Unit	Test Method
UL Flame Rating	0	-	UL-94
LOI	25	%	ASTM D-2863
Smoke Density (0.75 mm)	113 52	Flaming DM Non flaming DM	ASTM E662

Material Preparation

- Prior to processing, **ZHF58202 NAT02** must be dried at 100°C for 4 hours.
- It is recommended to dry the material in a dehumidifying type dryer. Target dew point should be **-40°C**.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

Material Preparation

- **ZHF58202 NAT02** can be processed on any conventional extruder.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



Recommended EXTRUSION Temperature Profile:

	°C
Zone 1	185
Zone 2	190
Zone 3	195
Zone 4	195
Adapter (5)	195
Die Zone 1 (6)	190
Die Zone 2	185

Storage

ZHF58202 NAT02 must be stored in a cool (15-25°C) and dry place. Standard Practice of consuming resin first-in first-out basis should be employed. Contact your account manager for specific information related to shelf life.

For further information refer to Lubrizol Advanced Materials processing guides.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>