

Technical Data Sheet

Type: Estane® S368D is a Shore 68D, polyester based thermoplastic polyurethane (TPU) with excellent transparency. FDA approved (21 CFR 177.2600, 177.1680)

Uses: Injection Molding

Physical Properties	Standard No.	Units	Value
Hardness	ASTM D2240	Shore D	68
Specific Gravity	ASTM D792	g/cm ³	1.27
Mechanical			
Tensile Stress:	ASTM D412	kgf/cm ²	
At 100% elongation			260
At 300% elongation			390
Tensile Strength	ASTM D412	kgf/cm ²	450
Ultimate Elongation	ASTM D412	%	380
Tear Resistance (Die C)	ASTM D624	kgf/cm	220
Abrasion Loss	ISO 4649	mm ³	25
Compression Set	ASTM D395		
At 23°C X22hr		%	25
At 70°C X22hr		%	40
Mold Shrinkage	ASTM D955	m/m	0.004
Thermal			
Vicat Softening Temperature	ASTM D1525	°C	125

*Test samples were annealed at 100°C and 24 hours at room temperature before testing.

**These are typical values and should not be used for specifications.

Injection Molding Guide

These settings are to be used only as a guide. This is a typical injection molding temperature profile based on the Test Machine (conditions based on a 75 ton machine with a general purpose screw – L/D 17 – Ø 35mm). The optimal run conditions for specific equipment will vary depending on the machine and mold design.

Drying Conditions

Drying	Conditions
Recommend 1	70-80°C for 4-5 hours by dehumidifying dryer

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



Injection Conditions

Barrel Temperature	
Feeding Zone	205~220
Metering Zone	215~230
Nozzle	220~235
Injection Conditions (I)	
Injection Pressure (psi)	1800-2400
Injection Speed	Moderate
Hold pressure (psi)	1300-1900
Injection Time(s)	12~18

Mold Temperature	
	10-40
Injection Conditions (II)	
Back Pressure (psi)	30-80
Screw Speed (rpm)	160-200
Cycle Time(s)	25-30

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
 All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>