

## Technical Data Sheet

**Type:** Estane® T470A is a Shore 77A, polyester grade, plasticizer-free, with low hardness thermoplastic polyurethane (TPU).

**Uses:** Injection Molding, Extrusion

Physical Properties	Standard No.	Units	Value
Hardness	ASTM D2240	Shore A	77
Specific Gravity	ASTM D792	g/cm <sup>3</sup>	1.13
<b>Mechanical</b>			
Tensile Stress:	ASTM D412	kgf/cm <sup>2</sup>	
At 100% elongation			36
At 300% elongation			60
Tensile Strength	ASTM D412	kgf/cm <sup>2</sup>	280
Ultimate Elongation	ASTM D412	%	900
Tear Resistance (Die C)	ASTM D624	kgf/cm	75
Compression Set	ASTM D395		
At 23°C X22hr		%	10
At 70°C X22hr		%	35
Mold Shrinkage	ASTM D955	m/m	0.006
<b>Thermal</b>			
Vicat Softening Temperature	ASTM D1525	°C	77

\*Test samples were annealed at 100°C and 24 hours at room temperature before testing.

\*\*These are typical values and should not be used for specifications.

## Injection Molding Guide

These settings are to be used only as a guide. This is a typical injection molding temperature profile based on the Test Machine (conditions based on a 75 ton machine with a general purpose screw – L/D 17 – Ø 35mm). The optimal run conditions for specific equipment will vary depending on the machine and mold design.

## Drying Conditions

Drying	Conditions
Recommend 1	70-80°C for 4-5 hours by dehumidifying dryer

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



### Injection Conditions

Barrel Temperature	
Feeding Zone	170~185
Metering Zone	175~190
Nozzle	180~195
Injection Conditions (I)	
Injection Pressure (psi)	1200~2000
Injection Speed	Slow
Hold pressure (psi)	800~1400
Injection Time(s)	15~20

Mold Temperature	
	10-40
Injection Conditions (II)	
Back Pressure (psi)	30-80
Screw Speed (rpm)	160-200
Cycle Time(s)	25-35

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

