

Technical Data Sheet

Pearlbond™ 580 is a linear, Polyester-based TPU, supplied in form of white spherical granules with a very high crystallization rate and a very high thermoplasticity level.

PRODUCT SPECIFICATION

Melt Flow Index (170°C/2.16 Kg)	10–30 g/10 min	ISO 1133
--	-----------------------	-----------------

PRODUCT CHARACTERISTICS

Property	Typical Values*	Test Method
Density @ 20°C	1.19 g/cm ³	ISO 2781
OH Value	< 3 mg KOH/g.	MQSA 47A
Moisture Content	< 0.15%	MQSA 44
Crystallization rate	14–18 min.	MQSA 12A
Melt Viscosity @ 130°C	2,700 Pa.s	ISO 1133
Melting Point	68 ± 3°C	MQSA 70A
Thermoplasticity	Very High	MQSA 68A

*These typical values provide general information, not for use as product specification.

APPLICATIONS

Pearlbond™ 580 can be added to formulations of REACTIVE POLYURETHANE HOT-MELTS (*HMPUR*), in order to improve the crystallisation speed.

HEALTH AND SAFETY

A safety data sheet on **Pearlbond™ 580** is available, with all safety information. The usual safety practices in the handling of chemicals should be observed, i.e.: good ventilation in the working area, gloves and protective goggles.

PACKAGING

Multifoil paper bags and PE bags containing 25 Kg.
Pallet of 750 Kg of weight.

STORAGE

Pearlbond™ 580 must be stored in a cool (15–25°C) and environment prior to being processed. Standard practice of consuming resin on first-in first-out basis should be employed.

For further information refer to Lubrizol Advanced Materials processing guides.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>