

Technical Data Sheet

Type: Pearlthane® ECO D12T80 is a high performance bio-based thermoplastic polyurethane.

With ca. 42% bio-based content.

Main Application: Injection Moulding

Special Features: Properties similar to standard TPU of same hardness, excellent mechanical properties and abrasion resistance.

Physical Properties*	Value (Metric)	Unit	Test Method
Hardness	A/1 : 82	Shore A/D	ISO 868
Specific Gravity	1.10	g/cm ³	ISO 2781
Tensile Strength	33	MPa	ISO 527-2/5A/500
Ultimate Elongation	604	%	ISO 527-2/5A/500
Tensile Stress at			
50 % Elongation	4	MPa	ISO 527-2/5A/500
100 % Elongation	4	MPa	ISO 527-2/5A/500
300 % Elongation	9	MPa	ISO 527-2/5A/500
Tear Strength Unnicked	84	kN/m	ISO 34-1B
Abrasion Resistance	20	mm ³	ISO 4649-A
Compression Set			
22h @ 100°C		%	ASTM D395B
70h @ 70°C		%	ASTM D395B
22h @ 70°C		%	ASTM D395B
Vicat Softening Point	84	°C	ISO 306 (A50)

*Based on moulded plaques.

Listed values are "typical (average) values" and should/can not be applied for specification purposes

See reverse side for processing information

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



Material Preparation

Prior to processing, Pearlthane® ECO D12T80 must be dried at 100°C during 3 hours. It is recommended to dry the material in a dehumidifying-type dryer. Target dew point to be below -30°C, preferably -40°C.

Recommended Injection Moulding Temperature Profile:

	°C
Feed zone	40
Zone 1	190
Zone 2	200
Zone 3	200
Zone 4	200
Nozzle	210

For further information, refer to Lubrizol Advanced Materials processing guides.

European version – Issue Date: 09/2015

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>