

Technical Data Sheet

Type: Estane[®] SKN 95C3 KR is 95A Polyester-Type Thermoplastic Polyurethane(TPU)

Features: High transparency

Uses: Injection molding, used for jelly case application

Physical Properties	Value (Metric)	Unit	Test Method
Hardness (5 sec)	95+/- 3	Shore A	ISO 868
Specific Gravity	1.22	g/cm3	ISO 2781
Tensile Strength	38	MPa	ISO 527
Ultimate Elongation	620	%	ISO 527
Tensile Stress at:			
- 100 % Elongation	10	MPa	ISO 527
- 300 % Elongation	17	MPa	ISO 527
Tear Strength			
Unicked	120	KN/m	ISO 34-1B

Remark

1. Prior to testing, Sample were conditioned at 23^oC, 50% humidity for 24 hours
2. Physical property test is based on 2mm injected plaque
3. Please be aware that the listed data is a "typical data" which should / cannot be applied for specification purpose

Supply Form and Standard Packaging

- Estane[®] SKN 95C3 KR is supplied in pellet form and packaged in 25 kg bags.

Material Preparation

- Prior to processing, Estane[®] SKN 95C3 KR must be dried at **100C** for 2-4 hours.
- It is recommended to dry the material in a desiccant type dryer. Target dew point should be **-40°C**.
- Depending on the applied processing technique, the maximum moisture level should be **0.02%**.

Material Preparation

- Estane[®] SKN 95C3 KR can be processed on any conventional injection machine.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>

Recommended Starting INJECTION MOLDING Temperature Profile:

	°C
Feed Zone 1	200
Zone 2	205
Zone 3	210
Nozzle	215

Fill rate: Moderate**For further information refer to Lubrizol Advanced Materials processing guides.**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.

<http://go.lubrizol.com/EP>