

Carbosperse[™] K-7600N Sodium Polyacrylate

Carbosperse K-7600N polyacrylate is a sodium salt of medium molecular weight water soluble acrylic acid polymer supplied as a clear, amber colored, 34% total solids solution in water.

Carbosperse K-7600N polyacrylate is a high performance polyelectrolyte with multi-functional properties including chelation, sequestration, dispersion, scale inhibition, crystal growth distortion, binding, and plasticizing.

The typical properties for Carbosperse K-7600N polyacrylate are as follows:

Form	Water solution
Appearance	Clear, amber colored
Total solids (%)	34 (33 to 35)*
Active solids (%)	26.7
Molecular weight** (GPC M _W)	120,000
рН	8.2 (7.5 to 9.0)*
Viscosity (cP at 25°C)	1,350 (950 to 1,750)*
Specific gravity	1.2 (1.1 to 1.3)

^{*} Specification.

CBSK7600N-TDS (Jun-07)

[™] Trademark of The Lubrizol Corporation

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, linc. shall not be liable for and the customer assumes all risks and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc. 4 side ricc control. The SELLER MAKES NO WARRANTIES, EVERES SOR IMPLIED, INCLUDINE IN TOT LIMITED TO, THE IMPLED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an influencement to practice any caterated investing without permission of the active lower.

^{**} Expressed as polyacrylic acid as determined by an aqueous GPC method.